


Stanyl® ForTii™ F31

PA4T-(GF+MF)35 FR

DSM Engineering Plastics

Product Texts

35% Glass/Mineral Reinforced, Halogen free and free of red phosphorous, Low Warpage

ISO 1043 PA4T-(GF+MF)35 FR

[Stanyl ForTii website](#)

Rheological properties	dry / cond	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.3 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	1.0 / *	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	12000 / 12000	MPa	ISO 527-1/-2
Stress at break	105 / 105	MPa	ISO 527-1/-2
Strain at break	1.3 / 1.3	%	ISO 527-1/-2
Charpy impact strength (+23°C)	25 / 25	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	5 / 5	kJ/m²	ISO 179/1eA
Thermal properties			
ISO Data			
Melting temperature (10°C/min)	325 / *	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	125 / *	°C	ISO 11357-1/-2
Temp. of deflection under load (1.80 MPa)	295 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	315 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	25 / *	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	45 / *	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	V-0 / *	class	IEC 60695-11-10
UL recognition	UL / *	-	-
Burning behav. at thickness h	V-0 / *	class	IEC 60695-11-10
Thickness tested	0.4 / *	mm	IEC 60695-11-10
UL recognition	UL / *	-	-
Oxygen index	39 / *	%	ISO 4589-1/-2
Electrical properties			
ISO Data			
Electric strength	33 / 33	kV/mm	IEC 60243-1
Comparative tracking index	600 / -	-	IEC 60112
Other properties			
ISO Data			
Humidity absorption	1.6 / *	%	Sim. to ISO 62
Density	1520 / -	kg/m³	ISO 1183
Material specific properties			
ISO Data			
Viscosity number	74 / *	cm³/g	ISO 307, 1157, 1628
Characteristics			
Processing		Additives	
Injection Molding		Lubricants, Release agent	

<div>Delivery form</div> <div>Granules</div>	<div>Special Characteristics</div> <div>Flame retardant</div>
----------------------------------------------	---------------------------------------------------------------