



TEREZ PA 6 7111 K

PA6

Ter Plastics

Product Texts

Polyamid without release agent for injection moulding and extrusion.

For all kind of moulding parts.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	3200	MPa	ISO 527-1/-2
Tensile Strength	80	MPa	ISO 527-1/-2
Yield strain	3	%	ISO 527-1/-2
Charpy impact strength (+23°C)	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	4	kJ/m ²	ISO 179/1eA

Other properties	Value	Unit	Test Standard
ISO Data			
Density	1130	kg/m ³	ISO 1183