


TEREZ PA 6 7400 GK 15 UV

PA6

Ter Plastics

Product Texts

Medium viscosity Polyamide 6, 15% glassbeads reinforced and UV stabilizer
 For distortion low moulding parts.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	3300	MPa	ISO 527-1/-2
Tensile Strength	75	MPa	ISO 527-1/-2
Yield stress	75	MPa	ISO 527-1/-2
Yield strain	2.4	%	ISO 527-1/-2
Strain at break	15	%	ISO 527-1/-2
Charpy impact strength (+23°C)	50	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	8	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load (1.80 MPa)	165	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	185	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	IEC 60695-11-10
Other properties			
ISO Data			
Water absorption	8	%	Sim. to ISO 62
Humidity absorption	2.7	%	Sim. to ISO 62
Density	1230	kg/m ³	ISO 1183