


TEREZ PA 6 7510 GF 20

PA6

Ter Plastics

Product Texts

 Medium viscosity PA6 with 20% glass fibre reinforcement.
 For moulding parts with high rigidity.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	6500	MPa	ISO 527-1/-2
Tensile Strength	130	MPa	ISO 527-1/-2
Yield stress	140	MPa	ISO 527-1/-2
Yield strain	2.5	%	ISO 527-1/-2
Strain at break	3.5	%	ISO 527-1/-2
Charpy impact strength (+23°C)	35	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	10	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load (1.80 MPa)	200	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	215	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	IEC 60695-11-10
Other properties			
ISO Data			
Water absorption	7.5	%	Sim. to ISO 62
Humidity absorption	2.2	%	Sim. to ISO 62
Density	1290	kg/m ³	ISO 1183