

**Technyl® C 218 V45**

PA6-GF45

Solvay Engineering Plastics

Product Texts

Polyamide PA6, reinforced with 45% of glass fibre. heat stabilised, for injection moulding.


Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	14400 / 9900	MPa	ISO 527-1/-2
Stress at break	220 / -	MPa	ISO 527-1/-2
Strain at break	3 / -	%	ISO 527-1/-2
Charpy impact strength (+23°C)	90 / -	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	16 / -	kJ/m ²	ISO 179/1eA

Thermal properties

ISO Data	dry / cond	Unit	Test Standard
Melting temperature (10°C/min)	222 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	210 / *	°C	ISO 75-1/-2

Other properties

ISO Data	dry / cond	Unit	Test Standard
Water absorption	0.7 / *	%	Sim. to ISO 62
Density	1470 / -	kg/m ³	ISO 1183

Diagrams**Stress-strain****Characteristics****Processing**

Injection Molding

Special Characteristics

Heat stabilized or stable to heat

Other text information**Injection Molding**

PROCESSING

Melt temperature: 225°C

Mold temperature: 80°C

Chemical Media Resistance

Acids

-  Acetic Acid (5% by mass) (23°C)
-  Citric Acid solution (10% by mass) (23°C)
-  Lactic Acid (10% by mass) (23°C)
-  Hydrochloric Acid (36% by mass) (23°C)
-  Nitric Acid (40% by mass) (23°C)
-  Sulfuric Acid (38% by mass) (23°C)
-  Sulfuric Acid (5% by mass) (23°C)
-  Chromic Acid solution (40% by mass) (23°C)

Bases

-  Sodium Hydroxide solution (35% by mass) (23°C)
-  Sodium Hydroxide solution (1% by mass) (23°C)
-  Ammonium Hydroxide solution (10% by mass) (23°C)

Alcohols

-  Isopropyl alcohol (23°C)
-  Methanol (23°C)
-  Ethanol (23°C)

Hydrocarbons

-  n-Hexane (23°C)
-  Toluene (23°C)
-  iso-Octane (23°C)

Ketones

-  Acetone (23°C)

Ethers

-  Diethyl ether (23°C)

Mineral oils

-  SAE 10W40 multigrade motor oil (23°C)

Standard Fuels

-  Standard fuel without alcohol (pref. ISO 1817 Liquid C) (23°C)
-  Standard fuel with alcohol (pref. ISO 1817 Liquid 4) (23°C)

Salt solutions

-  Zinc Chloride solution (50% by mass) (23°C)

Other

-  Ethylene Glycol (50% by mass) in water (108°C)
-  50% Oleic acid + 50% Olive Oil (23°C)
-  Water (23°C)
-  Deionized water (90°C)