


**TEREZ PA/PP 7510 GF 35**

(PA6+PP)

Ter Plastics

**Product Texts**

35 % glassfiber reinforced Blend, medium viscosity with high stiffness and low moisture absorption.  
 For moulding parts with high mechanical demand at low water absorption.

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	10500	MPa	ISO 527-1/-2
Tensile Strength	120	MPa	ISO 527-1/-2
Strain at break	5	%	ISO 527-1/-2
Charpy impact strength (+23°C)	60	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength (+23°C)	9	kJ/m <sup>2</sup>	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Vicat softening temperature A	188	°C	ISO 306

Other properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Density	1310	kg/m <sup>3</sup>	ISO 1183