


Akulon® S223-DH PA66				DSM Engineering Plastics
Product Texts				
Low/Medium Viscosity, Nucleated, Heat Stabilized				
ISO 1043 PA66				
Akulon website				
Rheological properties	dry / cond	Unit	Test Standard	
ISO Data				
Molding shrinkage, parallel	0.9 / *	%	ISO 294-4, 2577	
Molding shrinkage, normal	0.9 / *	%	ISO 294-4, 2577	
Mechanical properties				
ISO Data	dry / cond	Unit	Test Standard	
Tensile Modulus	3600 / 1500	MPa	ISO 527-1/-2	
Yield stress	95 / 60	MPa	ISO 527-1/-2	
Yield strain	3.5 / 20	%	ISO 527-1/-2	
Nominal strain at break	25 / >50	%	ISO 527-1/-2	
Charpy impact strength (+23°C)	N / N	kJ/m ²	ISO 179/1eU	
Charpy impact strength, -30°C	N / N	kJ/m ²	ISO 179/1eU	
Charpy notched impact strength (+23°C)	6 / 12	kJ/m ²	ISO 179/1eA	
Charpy notched impact strength, -30°C	6 / 6	kJ/m ²	ISO 179/1eA	
Thermal properties				
ISO Data	dry / cond	Unit	Test Standard	
Melting temperature (10°C/min)	260 / *	°C	ISO 11357-1/-3	
Temp. of deflection under load (1.80 MPa)	85 / *	°C	ISO 75-1/-2	
Temp. of deflection under load (0.45 MPa)	215 / *	°C	ISO 75-1/-2	
Coeff. of linear therm. expansion, parallel	100 / *	E-6/K	ISO 11359-1/-2	
Coeff. of linear therm. expansion, normal	100 / *	E-6/K	ISO 11359-1/-2	
Burning behav. at 1.5 mm nom. thickn.	V-2 / *	class	IEC 60695-11-10	
Thickness tested	1.5 / *	mm	IEC 60695-11-10	
UL recognition	UL / *	-	-	
Burning behav. at thickness h	HB / *	class	IEC 60695-11-10	
Thickness tested	0.7 / *	mm	IEC 60695-11-10	
UL recognition	UL / *	-	-	
Electrical properties				
ISO Data	dry / cond	Unit	Test Standard	
Relative permittivity, 100Hz	3.2 / 15	-	IEC 60250	
Relative permittivity, 1MHz	3 / 4.3	-	IEC 60250	
Dissipation factor, 100Hz	60 / 2400	E-4	IEC 60250	
Dissipation factor, 1MHz	170 / 1200	E-4	IEC 60250	
Volume resistivity	1E12 / 1E10	Ohm*m	IEC 60093	
Surface resistivity	* / 1E13	Ohm	IEC 60093	
Electric strength	30 / 25	kV/mm	IEC 60243-1	
Comparative tracking index	600 / 600	-	IEC 60112	
Other properties				
ISO Data	dry / cond	Unit	Test Standard	
Water absorption	8.5 / *	%	Sim. to ISO 62	
Humidity absorption	2.3 / *	%	Sim. to ISO 62	
Density	1140 / -	kg/m ³	ISO 1183	

Rheological calculation properties	Value	Unit	Test Standard
ISO Data			
Density of melt	969	kg/m ³	-
Thermal conductivity of melt	0.13	W/(m K)	-
Spec. heat capacity of melt	2750	J/(kg K)	-
Eff. thermal diffusivity	4.87E-8	m ² /s	-

Diagrams**Specific volume-temperature (pvT)****Characteristics****Processing**

Injection Molding

Additives

Release agent

Delivery form

Pellets

Special Characteristics

Heat stabilized or stable to heat

Other text information**Injection Molding**[Injection Molding Recommendations](#)