



Technyl® A 246M PA66		Solvay Engineering Plastics			
Product Texts					
Unreinforced and modified polyamide 6.6, with improved impact resistance					
Mechanical properties	dry / cond	Unit	Test Standard		
ISO Data					
Tensile Modulus	1900 / 600	MPa	ISO 527-1/-2		
Charpy impact strength (+23°C)	N / -	kJ/m <sup>2</sup>	ISO 179/1eU		
Charpy notched impact strength (+23°C)	55 / -	kJ/m <sup>2</sup>	ISO 179/1eA		
Thermal properties	dry / cond	Unit	Test Standard		
ISO Data					
Melting temperature (10°C/min)	263 / *	°C	ISO 11357-1/-3		
Temp. of deflection under load (1.80 MPa)	65 / *	°C	ISO 75-1/-2		
Coeff. of linear therm. expansion, parallel	70 / *	E-6/K	ISO 11359-1/-2		
Oxygen index	24.5 / *	%	ISO 4589-1/-2		
Electrical properties	dry / cond	Unit	Test Standard		
ISO Data					
Relative permittivity, 1MHz	3.2 / 4	-	IEC 60250		
Dissipation factor, 1MHz	200 / -	E-4	IEC 60250		
Volume resistivity	>1E13 / 1E13	Ohm*m	IEC 60093		
Surface resistivity	* / 1E13	Ohm	IEC 60093		
Electric strength	30 / 38	kV/mm	IEC 60243-1		
Comparative tracking index	600 / -	-	IEC 60112		
Other properties	dry / cond	Unit	Test Standard		
ISO Data					
Density	1080 / -	kg/m <sup>3</sup>	ISO 1183		
Test specimen production	Value	Unit	Test Standard		
ISO Data					
Injection Molding, melt temperature	245	°C	ISO 294		
Injection Molding, mold temperature	80	°C	ISO 10724		


## Technyl® A 246M

PA66


Solvay Engineering Plastics

### Diagrams


#### Viscosity-shear rate



#### Shearstress-shear rate



#### Stress-strain



### Characteristics

#### Processing

Injection Molding

#### Special Characteristics

Heat stabilized or stable to heat

#### Other text information

#### Injection Molding

PROCESSING

Melt temperature: 250°C

Mold temperature: 80°C

### Chemical Media Resistance

#### Acids

- Acetic Acid (5% by mass) (23°C)
- Citric Acid solution (10% by mass) (23°C)
- Lactic Acid (10% by mass) (23°C)
- Hydrochloric Acid (36% by mass) (23°C)
- Nitric Acid (40% by mass) (23°C)
- Sulfuric Acid (38% by mass) (23°C)
- Sulfuric Acid (5% by mass) (23°C)
- Chromic Acid solution (40% by mass) (23°C)

**Bases**

-  Sodium Hydroxide solution (35% by mass) (23°C)
-  Sodium Hydroxide solution (1% by mass) (23°C)
-  Ammonium Hydroxide solution (10% by mass) (23°C)

**Alcohols**

-  Isopropyl alcohol (23°C)
-  Methanol (23°C)
-  Ethanol (23°C)

**Hydrocarbons**

-  n-Hexane (23°C)
-  Toluene (23°C)
-  iso-Octane (23°C)

**Ketones**

-  Acetone (23°C)

**Ethers**

-  Diethyl ether (23°C)

**Mineral oils**

-  SAE 10W40 multigrade motor oil (23°C)

**Standard Fuels**

-  Standard fuel without alcohol (pref. ISO 1817 Liquid C) (23°C)
-  Standard fuel with alcohol (pref. ISO 1817 Liquid 4) (23°C)

**Salt solutions**

-  Zinc Chloride solution (50% by mass) (23°C)

**Other**

-  Ethylene Glycol (50% by mass) in water (108°C)
-  50% Oleic acid + 50% Olive Oil (23°C)
-  Water (23°C)
-  Deionized water (90°C)