

Arnite® TV4 244 SX PBT-GF20 FR(17)			
DSM Engineering Plastics			
Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	8600	MPa	ISO 527-1/2
Stress at break	110	MPa	ISO 527-1/2
Strain at break	2	%	ISO 527-1/2
Charpy impact strength (+23°C)	40	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	40	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	4.3	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	4.3	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Melting temperature (10°C/min)	225	°C	ISO 11357-1/3
Temp. of deflection under load (1.80 MPa)	210	°C	ISO 75-1/2
Temp. of deflection under load (0.45 MPa)	220	°C	ISO 75-1/2
Coeff. of linear therm. expansion, parallel	40	E-6/K	ISO 11359-1/2
Coeff. of linear therm. expansion, normal	80	E-6/K	ISO 11359-1/2
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.5	mm	IEC 60695-11-10
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.8	mm	IEC 60695-11-10
Electrical properties			
ISO Data			
Relative permittivity, 100Hz	3.9	-	IEC 60250
Relative permittivity, 1MHz	3.7	-	IEC 60250
Dissipation factor, 100Hz	20	E-4	IEC 60250
Dissipation factor, 1MHz	150	E-4	IEC 60250
Volume resistivity	>1E13	Ohm*m	IEC 60093
Electric strength	27	kV/mm	IEC 60243-1
Comparative tracking index	250	-	IEC 60112
Other properties			
ISO Data			
Water absorption	0.3	%	Sim. to ISO 62
Humidity absorption	0.15	%	Sim. to ISO 62
Density	1610	kg/m ³	ISO 1183
Characteristics			
Processing		Additives	
Injection Molding		Release agent	
Delivery form		Special Characteristics	
Pellets		Flame retardant	