


Arnite® TV4 264 SN

PBT-GF30 FR(17)

DSM Engineering Plastics

Product Texts

30% Glass Reinforced, Flame Retardant


ISO 1043 PBT-GF30 FR(17)

[Arnite website](#)


Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	11500	MPa	ISO 527-1/-2
Stress at break	130	MPa	ISO 527-1/-2
Strain at break	2	%	ISO 527-1/-2
Charpy impact strength (+23°C)	45	kJ/m²	ISO 179/1eU
Charpy impact strength, -30°C	45	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	8	kJ/m²	ISO 179/1eA
Charpy notched impact strength, -30°C	8	kJ/m²	ISO 179/1eA
Thermal properties			
ISO Data			
Melting temperature (10°C/min)	225	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	210	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	220	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	35	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	70	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.5	mm	IEC 60695-11-10
UL recognition	UL	-	-
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.8	mm	IEC 60695-11-10
UL recognition	UL	-	-
Electrical properties			
ISO Data			
Relative permittivity, 100Hz	3.7	-	IEC 60250
Relative permittivity, 1MHz	3.5	-	IEC 60250
Dissipation factor, 100Hz	20	E-4	IEC 60250
Dissipation factor, 1MHz	160	E-4	IEC 60250
Volume resistivity	>1E13	Ohm*m	IEC 60093
Comparative tracking index	200	-	IEC 60112
Other properties			
ISO Data			
Density	1700	kg/m³	ISO 1183
Rheological calculation properties			
ISO Data			
Density of melt	1440	kg/m³	-
Thermal conductivity of melt	0.153	W/(m K)	-
Spec. heat capacity of melt	1740	J/(kg K)	-
Eff. thermal diffusivity	6.12E-8	m²/s	-

Diagrams

Stress-strain



Secant modulus-strain



Characteristics

Processing

Injection Molding

Additives

Release agent

Delivery form

Pellets

Special Characteristics

Flame retardant

Other text information

Injection Molding

[Injection Molding Recommendations](#)