

| | | | | | | |
|---|--------------------------------|-------------------|----------------------|--|--|--|
| Arnite® TV6 241 SN | DSM Engineering Plastics | | | | | |
| PBT-GF20 FR(17) | | | | | | |
| Product Texts | | | | | | |
| 20% Glass Reinforced, Flame Retardant | | | | | | |
| ISO 1043 PBT-GF20 FR(17) | | | | | | |
| Arnite website | | | | | | |
| Mechanical properties | Value | Unit | Test Standard | | | |
| ISO Data | | | | | | |
| Tensile Modulus | 8500 | MPa | ISO 527-1/-2 | | | |
| Stress at break | 120 | MPa | ISO 527-1/-2 | | | |
| Strain at break | 2.5 | % | ISO 527-1/-2 | | | |
| Charpy impact strength (+23°C) | 50 | kJ/m ² | ISO 179/1eU | | | |
| Charpy impact strength, -30°C | 50 | kJ/m ² | ISO 179/1eU | | | |
| Charpy notched impact strength (+23°C) | 9 | kJ/m ² | ISO 179/1eA | | | |
| Charpy notched impact strength, -30°C | 7 | kJ/m ² | ISO 179/1eA | | | |
| Thermal properties | Value | Unit | Test Standard | | | |
| ISO Data | | | | | | |
| Melting temperature (10°C/min) | 225 | °C | ISO 11357-1/-3 | | | |
| Temp. of deflection under load (1.80 MPa) | 210 | °C | ISO 75-1/-2 | | | |
| Temp. of deflection under load (0.45 MPa) | 220 | °C | ISO 75-1/-2 | | | |
| Coeff. of linear therm. expansion, parallel | 40 | E-6/K | ISO 11359-1/-2 | | | |
| Coeff. of linear therm. expansion, normal | 80 | E-6/K | ISO 11359-1/-2 | | | |
| Burning behav. at 1.5 mm nom. thickn. | V-0 | class | IEC 60695-11-10 | | | |
| Thickness tested | 1.5 | mm | IEC 60695-11-10 | | | |
| UL recognition | UL | - | - | | | |
| Burning behav. at thickness h | V-2 | class | IEC 60695-11-10 | | | |
| Thickness tested | 0.8 | mm | IEC 60695-11-10 | | | |
| UL recognition | UL | - | - | | | |
| Electrical properties | Value | Unit | Test Standard | | | |
| ISO Data | | | | | | |
| Relative permittivity, 100Hz | 3.2 | - | IEC 60250 | | | |
| Relative permittivity, 1MHz | 3.2 | - | IEC 60250 | | | |
| Dissipation factor, 100Hz | 10 | E-4 | IEC 60250 | | | |
| Dissipation factor, 1MHz | 140 | E-4 | IEC 60250 | | | |
| Volume resistivity | >1E13 | Ohm*m | IEC 60093 | | | |
| Comparative tracking index | 250 | - | IEC 60112 | | | |
| Other properties | Value | Unit | Test Standard | | | |
| ISO Data | | | | | | |
| Water absorption | 0.4 | % | Sim. to ISO 62 | | | |
| Humidity absorption | 0.2 | % | Sim. to ISO 62 | | | |
| Density | 1620 | kg/m ³ | ISO 1183 | | | |
| Characteristics | | | | | | |
| Processing | Additives | | | | | |
| Injection Molding | Release agent | | | | | |
| Delivery form | Special Characteristics | | | | | |
| Pellets | Flame retardant | | | | | |

Arnite® TV6 241 SN

PBT-GF20 FR(17)

DSM Engineering Plastics

Other text information

Injection Molding

[Injection Molding Recommendations](#)