



PBT-5615			
PBT-GF15			ChangChun Group
Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0045	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.009	mm/mm	ASTM D 955
Density, 73°F	1400	kg/m ³	ASTM D 792
Water Absorption, 24hr	0.03	%	ASTM D 570
Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	74	MPa	ASTM D 638
Flexural Modulus	4415	MPa	ASTM D 790
Flexural Strength	118	MPa	ASTM D 790
Rockwell Hardness	M 85	-	ASTM D 785
Izod Impact notched, 1/4 in	0.0707	kJ/m	ASTM D 256
Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	1.6	mm	-
Coefficient of Thermal Expansion, MD	30	E-6/K	ASTM D 696
DTUL @ 66 psi	200	°C	ASTM D 648
DTUL @ 264 psi	190	°C	ASTM D 648
Melting Temperature	225	°C	ASTM D 3418
Electrical properties	Value	Unit	Test Standard
ASTM Data			
Dielectric Strength, Short Time	20	kV/mm	ASTM D 149
Dissipation Factor, 60 Hz	0.001	-	ASTM D 150
Dielectric Constant, 60 Hz	3.5	-	ASTM D 150
Surface Resistivity	1E13	Ohm	ASTM D 257
Volume Resistivity	>1E15	Ohm*cm	ASTM D 257
Arc Resistance	100	s	ASTM D 495
Characteristics			
Delivery form	Special Characteristics		
Pellets	Flame retardant		