



PBT-7320H			
PBT-GF20			ChangChun Group
Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.003	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.01	mm/mm	ASTM D 955
Density, 73°F	1330	kg/m ³	ASTM D 792
Water Absorption, 24hr	0.06	%	ASTM D 570
Mechanical properties			
ASTM Data	Value	Unit	Test Standard
Tensile Strength	78	MPa	ASTM D 638
Flexural Modulus	2453	MPa	ASTM D 790
Flexural Strength	118	MPa	ASTM D 790
Rockwell Hardness	M 90	-	ASTM D 785
Izod Impact notched, 1/4 in	0.0801	kJ/m	ASTM D 256
Thermal properties			
ASTM Data	Value	Unit	Test Standard
UL 94 Flame rating	HB	-	UL 94
Coefficient of Thermal Expansion, MD	30	E-6/K	ASTM D 696
DTUL @ 66 psi	200	°C	ASTM D 648
DTUL @ 264 psi	150	°C	ASTM D 648
Melting Temperature	225	°C	ASTM D 3418
Electrical properties			
ASTM Data	Value	Unit	Test Standard
Dielectric Strength, Short Time	20	kV/mm	ASTM D 149
Dissipation Factor, 60 Hz	0.001	-	ASTM D 150
Dielectric Constant, 60 Hz	4	-	ASTM D 150
Surface Resistivity	1E13	Ohm	ASTM D 257
Volume Resistivity	>1E15	Ohm*cm	ASTM D 257
Arc Resistance	90	s	ASTM D 495
Characteristics			
Delivery form	Features		
Pellets	Low Warpage		