



XANTAR® 24 R						
PC	Mitsubishi Engineering-Plastics Corporation					
Product Texts						
Medium Viscosity, Molding Release						
ISO 1043 PC						
XANTAR® Polycarbonate & Blends, your global partner for innovative added value						
Rheological properties	Value	Unit	Test Standard			
ISO Data						
Melt volume-flow rate, MVR	7	cm ³ /10min	ISO 1133			
Temperature	300	°C	ISO 1133			
Load	1.2	kg	ISO 1133			
Molding shrinkage, parallel	0.6	%	ISO 294-4, 2577			
Mechanical properties	Value	Unit	Test Standard			
ISO Data						
Tensile Modulus	2300	MPa	ISO 527-1/-2			
Yield stress	60	MPa	ISO 527-1/-2			
Yield strain	6	%	ISO 527-1/-2			
Nominal strain at break	>50	%	ISO 527-1/-2			
Thermal properties	Value	Unit	Test Standard			
ISO Data						
Temp. of deflection under load (1.80 MPa)	130	°C	ISO 75-1/-2			
Vicat softening temperature, 50°C/h 50N	150	°C	ISO 306			
Coeff. of linear therm. expansion, parallel	65	E-6/K	ISO 11359-1/-2			
Burning behav. at 1.5 mm nom. thickn.	V-2	class	IEC 60695-11-10			
Thickness tested	1.5	mm	IEC 60695-11-10			
UL recognition	UL	-	-			
Burning behav. at thickness h	V-2	class	IEC 60695-11-10			
Thickness tested	0.8	mm	IEC 60695-11-10			
UL recognition	UL	-	-			
Oxygen index	26	%	ISO 4589-1/-2			
Electrical properties	Value	Unit	Test Standard			
ISO Data						
Relative permittivity, 100Hz	3	-	IEC 60250			
Relative permittivity, 1MHz	2.9	-	IEC 60250			
Dissipation factor, 100Hz	6.6	E-4	IEC 60250			
Dissipation factor, 1MHz	92	E-4	IEC 60250			
Volume resistivity	>1E13	Ohm*m	IEC 60093			
Surface resistivity	>1E15	Ohm	IEC 60093			
Electric strength	29	kV/mm	IEC 60243-1			
Comparative tracking index	225	-	IEC 60112			
Other properties	Value	Unit	Test Standard			
ISO Data						
Water absorption	0.35	%	Sim. to ISO 62			
Density	1200	kg/m ³	ISO 1183			
Material specific properties	Value	Unit	Test Standard			
ISO Data						
Viscosity number	58	cm ³ /g	ISO 307, 1157, 1628			

XANTAR® 24 R


PC

Mitsubishi Engineering-Plastics Corporation


Rheological calculation properties	Value	Unit	Test Standard
ISO Data			
Density of melt	1010	kg/m ³	-
Thermal conductivity of melt	0.24	W/(m K)	-
Spec. heat capacity of melt	1710	J/(kg K)	-
Eff. thermal diffusivity	1.4E-7	m ² /s	-
Ejection temperature	131	°C	-
Test specimen production			
ISO Data			
Injection Molding, melt temperature	300	°C	ISO 294
Injection Molding, mold temperature	90	°C	ISO 10724

Diagrams


Viscosity-shear rate




Shearstress-shear rate




Stress-strain



Secant modulus-strain



Specific volume-temperature (pvT)



Characteristics

Processing

Injection Molding, Blow Molding

Additives

Release agent

Delivery form

Pellets

Special Characteristics

Heat stabilized or stable to heat, Transparent

Other text information

Injection Molding

[Injection Molding Recommendations](#)

Chemical Media Resistance

Acids

- Acetic Acid (5% by mass) (23°C)
- Citric Acid solution (10% by mass) (23°C)
- Lactic Acid (10% by mass) (23°C)
- Hydrochloric Acid (36% by mass) (23°C)
- Nitric Acid (40% by mass) (23°C)
- Sulfuric Acid (38% by mass) (23°C)
- Sulfuric Acid (5% by mass) (23°C)
- Chromic Acid solution (40% by mass) (23°C)

Bases

- Sodium Hydroxide solution (35% by mass) (23°C)
- Sodium Hydroxide solution (1% by mass) (23°C)
- Ammonium Hydroxide solution (10% by mass) (23°C)

Alcohols

- Isopropyl alcohol (23°C)
- Methanol (23°C)
- Ethanol (23°C)

Hydrocarbons

- n-Hexane (23°C)
- Toluene (23°C)
- iso-Octane (23°C)

Ketones

- Acetone (23°C)

Ethers

 Diethyl ether (23°C)

Salt solutions

-  Sodium Chloride solution (10% by mass) (23°C)
-  Sodium Hypochlorite solution (10% by mass) (23°C)
-  Sodium Carbonate solution (20% by mass) (23°C)
-  Sodium Carbonate solution (2% by mass) (23°C)
-  Zinc Chloride solution (50% by mass) (23°C)

Other

-  Ethyl Acetate (23°C)
-  Hydrogen peroxide (23°C)
-  Water (23°C)
-  Phenol solution (5% by mass) (23°C)