


TEREZ PC/ABS Blend 2000 GF 10

(PC+ABS)

Ter Plastics

Product Texts

 Heat distortion resistant PC/ABS Blend with 10%GF reinforce
 For all kind of injection moulding parts with increased requirements of stiffness

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	20	g/10min	ISO 1133
MFI temperature	250	°C	ISO 1133
MFI load	5	kg	ISO 1133
Mechanical properties			
ISO Data			
Tensile Modulus	3900	MPa	ISO 527-1/-2
Yield stress	65	MPa	ISO 527-1/-2
Yield strain	3	%	ISO 527-1/-2
Strain at break	4	%	ISO 527-1/-2
Charpy impact strength (+23°C)	28	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	14	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load (1.80 MPa)	118	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	130	°C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	129	°C	ISO 306
Other properties			
ISO Data			
Density	1200	kg/m ³	ISO 1183