



XANTAR® C CF 107 (PC+ABS) FR(40)...	Mitsubishi Engineering-Plastics Corporation					
Product Texts						
Flame Retardant, High Flow						
ISO 1043 (PC+ABS) FR(40)...						
<u>XANTAR® Polycarbonate & Blends, your global partner for innovative added value</u>						
Rheological properties	Value	Unit	Test Standard			
ISO Data						
Melt volume-flow rate, MVR	50	cm ³ /10min	ISO 1133			
Temperature	260	°C	ISO 1133			
Load	5	kg	ISO 1133			
Molding shrinkage, parallel	0.5	%	ISO 294-4, 2577			
Mechanical properties	Value	Unit	Test Standard			
ISO Data						
Tensile Modulus	2850	MPa	ISO 527-1/-2			
Yield stress	60	MPa	ISO 527-1/-2			
Yield strain	4	%	ISO 527-1/-2			
Nominal strain at break	>50	%	ISO 527-1/-2			
Charpy impact strength (+23°C)	N	kJ/m ²	ISO 179/1eU			
Charpy impact strength, -30°C	N	kJ/m ²	ISO 179/1eU			
Thermal properties	Value	Unit	Test Standard			
ISO Data						
Temp. of deflection under load (1.80 MPa)	90	°C	ISO 75-1/-2			
Vicat softening temperature, 50°C/h 50N	104	°C	ISO 306			
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10			
Thickness tested	1.5	mm	IEC 60695-11-10			
UL recognition	UL	-	-			
Burning behav. at thickness h	V-0	class	IEC 60695-11-10			
Thickness tested	3.0	mm	IEC 60695-11-10			
UL recognition	UL	-	-			
Burning behav. 5V at thickness h	5VB	class	IEC 60695-11-20			
Thickness tested	2.0	mm	IEC 60695-11-20			
UL recognition	UL	-	-			
Oxygen index	32	%	ISO 4589-1/-2			
Electrical properties	Value	Unit	Test Standard			
ISO Data						
Relative permittivity, 1MHz	3	-	IEC 60250			
Volume resistivity	>1E13	Ohm*m	IEC 60093			
Surface resistivity	>1E15	Ohm	IEC 60093			
Comparative tracking index	575	-	IEC 60112			
Other properties	Value	Unit	Test Standard			
ISO Data						
Water absorption	0.6	%	Sim. to ISO 62			
Humidity absorption	0.2	%	Sim. to ISO 62			
Density	1170	kg/m ³	ISO 1183			
Rheological calculation properties	Value	Unit	Test Standard			
ISO Data						
Density of melt	1000	kg/m ³	-			





XANTAR® C CF 107

(PC+ABS) FR(40)...


Mitsubishi Engineering-Plastics Corporation

Thermal conductivity of melt	0.23	W/(m K)	-
Spec. heat capacity of melt	2220	J/(kg K)	-
Eff. thermal diffusivity	1E-7	m ² /s	-
Ejection temperature	95	°C	-

Test specimen production	Value	Unit	Test Standard
ISO Data			
Injection Molding, melt temperature	270	°C	ISO 294
Injection Molding, mold temperature	70	°C	ISO 10724

Diagrams**Viscosity-shear rate****Shearstress-shear rate****Stress-strain****Secant modulus-strain**

Specific volume-temperature (pvT)



Characteristics

Processing

Injection Molding

Additives

Release agent

Delivery form

Pellets

Special Characteristics

Flame retardant

Other text information

Injection Molding

[Injection Molding Recommendations](#)