



PLEXIGLAS® Heatresist hw55

PMMA

Evonik Industries AG

Product Texts

Productprofil:

PLEXIGLAS® Heatresist hw55 clear is a copolymer based on methyl methacrylate (MMA) with comonomer constituents.

Besides showing the familiar properties of standard PLEXIGLAS® molding compound, such as

- high light transmission,
- good flowability,
- high mechanical strength, surface hardness and abrasion resistance, as well as
- excellent weatherability,

PLEXIGLAS® Heatresist hw55 clear offers the additional benefits of

- increased heat deflection temperature under load and
- improved resistance to stress cracking
- optimised inherent color,
- AMECA listing.

Application:

PLEXIGLAS® Heatresist hw55 clear is particularly suitable for injection molding of technical items.

Example:

lighted keys, luminaire covers, fiber optics.

Processing:

PLEXIGLAS® Heatresist hw55 clear can be processed on injection molding machines with 3-zone general purpose screws for thermoplastics.

Physical Form / Packaging:


PLEXIGLAS® Heatresist hw55 is supplied as pellets of uniform size, packaged in two-ply, 25kg polyethylene bags; other packaging on request.

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	1.2	cm ³ /10min	ISO 1133
Temperature	230	°C	ISO 1133
Load	3.8	kg	ISO 1133
Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	3600	MPa	ISO 527-1/-2
Stress at break	80	MPa	ISO 527-1/-2
Strain at break	3.5	%	ISO 527-1/-2
Tensile creep modulus, 1h	3300	MPa	ISO 899-1
Tensile creep modulus, 1000h	2700	MPa	ISO 899-1
Charpy impact strength (+23°C)	20	kJ/m ²	ISO 179/1eU
Thermal properties	Value	Unit	Test Standard
ISO Data			
Glass transition temperature, 10°C/min	122	°C	ISO 11357-1/-2
Temp. of deflection under load (1.80 MPa)	106	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	109	°C	ISO 75-1/-2


PLEXIGLAS® Heatresist hw55			
PMMA	Evonik Industries AG		
Vicat softening temperature, 50°C/h 50N	119	°C	ISO 306
Coeff. of linear therm. expansion, parallel	70	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	IEC 60695-11-10
UL recognition	UL	-	-
Oxygen index	18	%	ISO 4589-1/-2
Electrical properties			
ISO Data	Value	Unit	Test Standard
Relative permittivity, 100Hz	3.5	-	IEC 60250
Relative permittivity, 1MHz	2.9	-	IEC 60250
Dissipation factor, 100Hz	400	E-4	IEC 60250
Dissipation factor, 1MHz	200	E-4	IEC 60250
Volume resistivity	>1E13	Ohm*m	IEC 60093
Surface resistivity	1E13	Ohm	IEC 60093
Comparative tracking index	600	-	IEC 60112
Other properties			
ISO Data	Value	Unit	Test Standard
Water absorption	2.2	%	Sim. to ISO 62
Humidity absorption	0.6	%	Sim. to ISO 62
Density	1190	kg/m³	ISO 1183
Material specific properties			
ISO Data	Value	Unit	Test Standard
Viscosity number	60	cm³/g	ISO 307, 1157, 1628
Luminous transmittance	90	%	ISO 13468-1, -2
Rheological calculation properties			
ISO Data	Value	Unit	Test Standard
Density of melt	1080	kg/m³	-
Thermal conductivity of melt	0.19	W/(m K)	-
Spec. heat capacity of melt	2440	J/(kg K)	-
Eff. thermal diffusivity	7.22E-8	m²/s	-
Ejection temperature	100	°C	-
Test specimen production			
ISO Data	Value	Unit	Test Standard
Injection Molding, melt temperature	250	°C	ISO 294
Injection Molding, mold temperature	82	°C	ISO 10724
Injection Molding, injection velocity	195	mm/s	ISO 294

Diagrams


Viscosity-shear rate




Shearstress-shear rate




Dynamic Shear modulus-temperature




Stress-strain



Secant modulus-strain



Specific volume-temperature (pvT)




PLEXIGLAS® Heatresist hw55


PMMA

Evonik Industries AG

Spec. enthalpy/mass-temp. (DSC)



Tensile modulus-temperature



Characteristics

Processing

Injection Molding

Special Characteristics

Light stabilized or stable to light, U.V. stabilized or stable to weather, Heat stabilized or stable to heat, Transparent

Delivery form

Pellets

Other text information

Injection Molding

PREPROCESSING

Predrying temperature: max. 109 °C

Predrying time in a desiccant-type drier: 2 - 3 h

PROCESSING

Min. melt temperature: 220 - 250°C

Min. mold temperature: 60 - 90°C

Chemical Media Resistance

Acids

- 😊 Citric Acid solution (10% by mass) (23°C)
- 😊 Lactic Acid (10% by mass) (23°C)
- 😊 Nitric Acid (40% by mass) (23°C)
- 😊 Sulfuric Acid (38% by mass) (23°C)
- 😊 Sulfuric Acid (5% by mass) (23°C)

Bases

- 😊 Sodium Hydroxide solution (35% by mass) (23°C)
- 😊 Sodium Hydroxide solution (1% by mass) (23°C)
- 😊 Ammonium Hydroxide solution (10% by mass) (23°C)

Hydrocarbons

- 😊 n-Hexane (23°C)
- 😊 iso-Octane (23°C)

Standard Fuels

- 😊 Standard fuel without alcohol (pref. ISO 1817 Liquid C) (23°C)
- 😊 Standard fuel with alcohol (pref. ISO 1817 Liquid 4) (23°C)
- 😊 Diesel fuel (pref. ISO 1817 Liquid F) (23°C)

Salt solutions

- 😊 Sodium Carbonate solution (20% by mass) (23°C)
- 😊 Sodium Carbonate solution (2% by mass) (23°C)

PLEXIGLAS® Heatresist hw55

PMMA

Evonik Industries AG

Other

-  50% Oleic acid + 50% Olive Oil (23°C)
-  Water (23°C)