

**PLEXIGLAS® Resist zk30**

PMMA-I

Evonik Industries AG

Product Texts**Productprofil:**

PLEXIGLAS® Resist zk30 is an amorphous, impact-modified thermoplastic molding compound (PMMA-I).

Typical properties of impact-modified PLEXIGLAS® molding compounds are:

- excellent transmission and clarity
- brilliant appearance
- the pleasant feel and sound of the moldings.

PLEXIGLAS® Resist zk30 is characterized by the following special properties:

- good break resistance and impact strength
- improved resistance to stress cracking
- certified dishwasher resistance
- AMECA listing.

Application:

Used for injection molding. Profile extrusion or coextrusion are also possible.

Example:

lighting fixtures, writing and drawing utensils, domestic appliances and sanitaryware

Processing:

PLEXIGLAS® Resist zk30 can be processed on machines with 3-zone general purpose screws for engineering thermoplastics.

Physical Form / Packaging:

PLEXIGLAS® Resist zk30 molding compounds are supplied as pellets of uniform size, packaged in 25kg polyethylene bags or 500kg boxes with PE lining; other packaging on request.

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	1.4	cm ³ /10min	ISO 1133
Temperature	230	°C	ISO 1133
Load	3.8	kg	ISO 1133
Mechanical properties			
ISO Data			
Tensile Modulus	2000	MPa	ISO 527-1/-2
Yield stress	51	MPa	ISO 527-1/-2
Yield strain	4.5	%	ISO 527-1/-2
Nominal strain at break	27	%	ISO 527-1/-2
Tensile creep modulus, 1h	1900	MPa	ISO 899-1
Tensile creep modulus, 1000h	1300	MPa	ISO 899-1
Charpy impact strength (+23°C)	55	kJ/m ²	ISO 179/1eU
Thermal properties			
ISO Data			
Glass transition temperature, 10°C/min	114	°C	ISO 11357-1/-2
Temp. of deflection under load (1.80 MPa)	91	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	96	°C	ISO 75-1/-2

PLEXIGLAS® Resist zk30			
PMMA-I			
Evonik Industries AG			
Vicat softening temperature, 50°C/h 50N	98	°C	ISO 306
Coeff. of linear therm. expansion, parallel	110	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	IEC 60695-11-10
Oxygen index	17.5	%	ISO 4589-1/-2
Electrical properties			
ISO Data			
Relative permittivity, 100Hz	3.7	-	IEC 60250
Relative permittivity, 1MHz	2.9	-	IEC 60250
Dissipation factor, 100Hz	500	E-4	IEC 60250
Dissipation factor, 1MHz	300	E-4	IEC 60250
Volume resistivity	>1E13	Ohm*m	IEC 60093
Surface resistivity	1E13	Ohm	IEC 60093
Comparative tracking index	600	-	IEC 60112
Other properties			
ISO Data			
Water absorption	1.7	%	Sim. to ISO 62
Humidity absorption	0.5	%	Sim. to ISO 62
Density	1150	kg/m³	ISO 1183
Material specific properties			
ISO Data			
Luminous transmittance	90	%	ISO 13468-1, -2
Rheological calculation properties			
ISO Data			
Density of melt	1040	kg/m³	-
Thermal conductivity of melt	0.19	W/(m K)	-
Spec. heat capacity of melt	2440	J/(kg K)	-
Eff. thermal diffusivity	7.49E-8	m²/s	-
Ejection temperature	80	°C	-
Test specimen production			
ISO Data			
Injection Molding, melt temperature	250	°C	ISO 294
Injection Molding, mold temperature	58	°C	ISO 10724
Injection Molding, injection velocity	195	mm/s	ISO 294


PLEXIGLAS® Resist zk30

PMMA-I


Evonik Industries AG

Diagrams


Viscosity-shear rate




Shearstress-shear rate




Dynamic Shear modulus-temperature




Stress-strain



Secant modulus-strain



Stress-strain (isochronous) 23°C




PLEXIGLAS® Resist zk30


PMMA-I

Evonik Industries AG

Creep modulus-time 23°C



Tensile modulus-temperature



Characteristics

Processing

Injection Molding, Profile Extrusion, Sheet Extrusion, Other Extrusion, Thermoforming

Additives

Release agent

Delivery form

Pellets

Special Characteristics

High impact or impact modified, Light stabilized or stable to light, U.V. stabilized or stable to weather, Transparent

Other text information

Injection Molding

PREPROCESSING

Predrying temperature: max. 90 °C

Predrying time in a desiccant-type drier: 2 - 3 h

PROCESSING

Min. melt temperature: 230 - 240°C

Min. mold temperature: 50 - 70°C

Profile extrusion

PREPROCESSING

Predrying temperature: max. 90 °C

Predrying time in a desiccant-type drier: 2 - 3 h

PROCESSING

Melt temperature: 230 - 240 °C

Die temperature: 230 - 240 °C

Sheet extrusion

PREPROCESSING

Predrying temperature: max. 90 °C

Predrying time in a desiccant-type drier: 2 - 3 h

PROCESSING

Melt temperature: 230 - 240 °C

Die temperature: 230 - 240 °C

Chemical Media Resistance

Acids

- 😊 Citric Acid solution (10% by mass) (23°C)
- 😊 Lactic Acid (10% by mass) (23°C)
- 😊 Sulfuric Acid (38% by mass) (23°C)
- 😊 Sulfuric Acid (5% by mass) (23°C)

Bases

- 😊 Sodium Hydroxide solution (35% by mass) (23°C)
- 😊 Sodium Hydroxide solution (1% by mass) (23°C)
- 😊 Ammonium Hydroxide solution (10% by mass) (23°C)

PLEXIGLAS® Resist zk30

PMMA-I

Evonik Industries AG

Hydrocarbons

-  n-Hexane (23°C)

Standard Fuels

-  Standard fuel without alcohol (pref. ISO 1817 Liquid C) (23°C)
-  Standard fuel with alcohol (pref. ISO 1817 Liquid 4) (23°C)
-  Diesel fuel (pref. ISO 1817 Liquid F) (23°C)

Other

-  50% Oleic acid + 50% Olive Oil (23°C)
-  Water (23°C)