

**PLEXIGLAS® Resist zk6HC**

PMMA-I

Evonik Industries AG

Product Texts**Productprofil:**

PLEXIGLAS® Resist zk6HC is an amorphous, impact-modified thermoplastic molding compounds (PMMA-I).

Typical properties of impact-modified PLEXIGLAS® molding compounds are

- high weather resistance
- excellent transmission and clarity
- brilliant appearance
- the pleasant feel and sound of the moldings.

PLEXIGLAS® Resist zk6HC is characterized by the following special properties:

- excellent break resistance and impact strength
- best resistance to stress cracking of all impact-modified PLEXIGLAS® molding compounds.

Application:

Used for extruding and coextruding sheets and profiles

Example:

extruded/coextruded sheets and profiles for automotive bodies and the sanitaryware sector (bathtubs and shower trays) or crystal-clear luminaire covers for industrial plants that come into contact with aggressive media.

Processing:

PLEXIGLAS® Resist zk6HC can be processed on machines with 3-zone general purpose screws for engineering thermoplastics.

Physical Form / Packaging:

PLEXIGLAS® Resist zk molding compounds are supplied as pellets of uniform size in 25kg polyethylene bags or in 500kg boxes with PE lining; other packaging on request.

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	0.4	cm ³ /10min	ISO 1133
Temperature	230	°C	ISO 1133
Load	3.8	kg	ISO 1133
Mechanical properties			
ISO Data			
Tensile Modulus	2000	MPa	ISO 527-1/-2
Yield stress	47	MPa	ISO 527-1/-2
Yield strain	5.5	%	ISO 527-1/-2
Nominal strain at break	48	%	ISO 527-1/-2
Charpy impact strength (+23°C)	80	kJ/m ²	ISO 179/1eU
Thermal properties			
ISO Data			
Glass transition temperature, 10°C/min	95	°C	ISO 11357-1/-2
Temp. of deflection under load (1.80 MPa)	93	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	98	°C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	97	°C	ISO 306
Coeff. of linear therm. expansion, parallel	110	E-6/K	ISO 11359-1/-2

PLEXIGLAS® Resist zk6HC			
PMMA-I			
Evonik Industries AG			
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	IEC 60695-11-10
UL recognition	UL	-	-
Oxygen index	17.5	%	ISO 4589-1/-2
Electrical properties			
ISO Data	Value	Unit	Test Standard
Relative permittivity, 100Hz	3.7	-	IEC 60250
Relative permittivity, 1MHz	2.9	-	IEC 60250
Dissipation factor, 100Hz	500	E-4	IEC 60250
Dissipation factor, 1MHz	300	E-4	IEC 60250
Volume resistivity	>1E13	Ohm*m	IEC 60093
Surface resistivity	1E13	Ohm	IEC 60093
Other properties			
ISO Data	Value	Unit	Test Standard
Water absorption	1.8	%	Sim. to ISO 62
Humidity absorption	0.5	%	Sim. to ISO 62
Density	1160	kg/m ³	ISO 1183
Material specific properties			
ISO Data	Value	Unit	Test Standard
Luminous transmittance	91	%	ISO 13468-1, -2
Rheological calculation properties			
ISO Data	Value	Unit	Test Standard
Density of melt	1040	kg/m ³	-
Thermal conductivity of melt	0.19	W/(m K)	-
Spec. heat capacity of melt	2440	J/(kg K)	-
Eff. thermal diffusivity	7.49E-8	m ² /s	-
Ejection temperature	75	°C	-
Test specimen production			
ISO Data	Value	Unit	Test Standard
Injection Molding, melt temperature	252	°C	ISO 294
Injection Molding, mold temperature	57	°C	ISO 10724
Injection Molding, injection velocity	195	mm/s	ISO 294


PLEXIGLAS® Resist zk6HC

PMMA-I


Evonik Industries AG

Diagrams


Viscosity-shear rate




Shearstress-shear rate




Dynamic Shear modulus-temperature




Stress-strain



Secant modulus-strain



Tensile modulus-temperature



Characteristics

Created: 2015-08-15 Source: www.materialdatacenter.com

Page: 3/4

Our product information and suggestions are based on analyses, empirical values, and data from the product manufacturer in question and are therefore provided with our best knowledge and accountability. We do not, however, assume any liability or warranty, be it for defects in title, quality and suitability of the products for a specific purpose, or non-infringement of industrial property rights. We do not warrant the use or processing of the products and information, or consequences of any kind arising from product descriptions, suggestions, and recommendations. The responsibility for appropriate usage, as well as final suitability testing of the raw material is exclusively the responsibility of the customer as part of sampling/ final qualification of a manufactured molded part. The specified data are only indicative and are not to be interpreted as legally binding specifications.

PLEXIGLAS® Resist zk6HC

PMMA-I

Evonik Industries AG

Processing

Film Extrusion, Profile Extrusion, Sheet Extrusion, Other Extrusion

Additives

Release agent

Delivery form

Pellets

Special Characteristics

High impact or impact modified, Light stabilized or stable to light, U.V. stabilized or stable to weather, Transparent

Other text information

Profile extrusion

PREPROCESSING

Predrying temperature: max. 85 °C

Predrying time in a desiccant-type drier: 2 - 3 h

PROCESSING

Melt temperature: 220 - 260 °C

Die temperature: 220 - 260 °C

Sheet extrusion

PREPROCESSING

Predrying temperature: max. 85 °C

Predrying time in a desiccant-type drier: 2 - 3 h

PROCESSING

Melt temperature: 220 - 260 °C

Die temperature: 220 - 260 °C

Chemical Media Resistance

Acids

-  Acetic Acid (5% by mass) (23°C)
-  Citric Acid solution (10% by mass) (23°C)
-  Lactic Acid (10% by mass) (23°C)
-  Hydrochloric Acid (36% by mass) (23°C)
-  Sulfuric Acid (38% by mass) (23°C)
-  Sulfuric Acid (5% by mass) (23°C)

Bases

-  Sodium Hydroxide solution (35% by mass) (23°C)
-  Sodium Hydroxide solution (1% by mass) (23°C)
-  Ammonium Hydroxide solution (10% by mass) (23°C)

Hydrocarbons

-  n-Hexane (23°C)
-  iso-Octane (23°C)

Mineral oils

-  SAE 10W40 multigrade motor oil (23°C)

Standard Fuels

-  Standard fuel without alcohol (pref. ISO 1817 Liquid C) (23°C)
-  Standard fuel with alcohol (pref. ISO 1817 Liquid 4) (23°C)

Salt solutions

-  Sodium Carbonate solution (20% by mass) (23°C)
-  Sodium Carbonate solution (2% by mass) (23°C)

Other

-  50% Oleic acid + 50% Olive Oil (23°C)
-  Water (23°C)