

**PLEXIGLAS® Satinice df23 8N**

PMMA

Evonik Industries AG

Product Texts**Productprofil:**

PLEXIGLAS® Satinice df23 8N, based on PLEXIGLAS® 8N, is characterized by diffuse scattering of light.

Typical properties of PLEXIGLAS® molding compound are

- good flow
- high mechanical strength, surface hardness and mar resistance
- very good weather resistance.

Special properties of PLEXIGLAS® Satinice df23 8N are

- excellent lightdiffusion combined with excellent light transmission.

Application:

Used for injection molding items for lighting engineering applications

Example:

luminaire covers, projection screens and similar applications

Processing:

PLEXIGLAS® Satinice df23 8N can be processed on injection molding machines with 3-zone general purpose screws for engineering thermoplastics.

Physical Form / Packaging:

PLEXIGLAS® Satinice df molding compounds are supplied as pellets of uniform size, packaged in 25kg polyethylene bags; other packaging on request.

| Rheological properties | Value | Unit | Test Standard |
|---|-------|------------------------|----------------|
| ISO Data | | | |
| Melt volume-flow rate, MVR | 2.1 | cm ³ /10min | ISO 1133 |
| Temperature | 230 | °C | ISO 1133 |
| Load | 3.8 | kg | ISO 1133 |
| Mechanical properties | | | |
| ISO Data | | | |
| Tensile Modulus | 3300 | MPa | ISO 527-1/-2 |
| Stress at break | 65 | MPa | ISO 527-1/-2 |
| Strain at break | 2.5 | % | ISO 527-1/-2 |
| Charpy impact strength (+23°C) | 16 | kJ/m ² | ISO 179/1eU |
| Thermal properties | | | |
| ISO Data | | | |
| Glass transition temperature, 10°C/min | 108 | °C | ISO 11357-1/-2 |
| Temp. of deflection under load (1.80 MPa) | 98 | °C | ISO 75-1/-2 |
| Temp. of deflection under load (0.45 MPa) | 103 | °C | ISO 75-1/-2 |
| Vicat softening temperature, 50°C/h 50N | 109 | °C | ISO 306 |
| Coeff. of linear therm. expansion, parallel | 63 | E-6/K | ISO 11359-1/-2 |
| Electrical properties | | | |
| ISO Data | | | |

PLEXIGLAS® Satinice df23 8N

PMMA

Evonik Industries AG

| | | | |
|---------------------|-------|-------|-----------|
| Volume resistivity | >1E13 | Ohm*m | IEC 60093 |
| Surface resistivity | 1E13 | Ohm | IEC 60093 |

Other properties

ISO Data

| | | | |
|---------|------|-------------------|----------|
| Density | 1190 | kg/m ³ | ISO 1183 |
|---------|------|-------------------|----------|

Material specific properties

ISO Data

| | | | |
|------------------------|----|---|-----------------|
| Luminous transmittance | 81 | % | ISO 13468-1, -2 |
|------------------------|----|---|-----------------|

VDA Properties

ISO Data

| | | | |
|------------------------------|------|--------|----------------------|
| Burning rate, Thickness 1 mm | 73.4 | mm/min | ISO 3795 (FMVSS 302) |
|------------------------------|------|--------|----------------------|


Test specimen production

ISO Data


| | | | |
|---------------------------------------|-----|------|-----------|
| Injection Molding, melt temperature | 248 | °C | ISO 294 |
| Injection Molding, mold temperature | 69 | °C | ISO 10724 |
| Injection Molding, injection velocity | 195 | mm/s | ISO 294 |

Diagrams


Viscosity-shear rate




Shearstress-shear rate



Dynamic Shear modulus-temperature



Stress-strain




PLEXIGLAS® Satinice df23 8N


PMMA

Evonik Industries AG

Secant modulus-strain



Tensile modulus-temperature



Characteristics

Processing

Injection Molding

Additives

Release agent

Delivery form

Pellets

Special Characteristics

Light stabilized or stable to light, U.V. stabilized or stable to weather

Other text information

Injection Molding

PREPROCESSING

Predrying temperature: max. 95 °C

Predrying time in a desiccant-type drier: 2 - 3 h

PROCESSING

Min. melt temperature: 220 - 260°C

Min. mold temperature: 60 - 90°C

Chemical Media Resistance

Acids

- 😊 Acetic Acid (5% by mass) (23°C)
- 😊 Citric Acid solution (10% by mass) (23°C)
- 😊 Lactic Acid (10% by mass) (23°C)
- 😊 Sulfuric Acid (38% by mass) (23°C)
- 😊 Sulfuric Acid (5% by mass) (23°C)

Bases

- 😊 Sodium Hydroxide solution (35% by mass) (23°C)
- 😊 Sodium Hydroxide solution (1% by mass) (23°C)
- 😊 Ammonium Hydroxide solution (10% by mass) (23°C)

Hydrocarbons

- 😊 n-Hexane (23°C)
- 😊 iso-Octane (23°C)

Standard Fuels

- 😊 Standard fuel without alcohol (pref. ISO 1817 Liquid C) (23°C)
- 😊 Standard fuel with alcohol (pref. ISO 1817 Liquid 4) (23°C)
- 😊 Diesel fuel (pref. ISO 1817 Liquid F) (23°C)

PLEXIGLAS® Satinice df23 8N

PMMA

Evonik Industries AG

Salt solutions

-  Sodium Carbonate solution (20% by mass) (23°C)
-  Sodium Carbonate solution (2% by mass) (23°C)

Other

-  50% Oleic acid + 50% Olive Oil (23°C)
-  Water (23°C)