



DURACon® GH-10 POM-GF10			
Polyplastics			
Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Strength	92	MPa	ISO 527-1/-2
Strain at break	3.7	%	ISO 527-1/-2
Charpy notched impact strength (+23°C)	4.8	kJ/m <sup>2</sup>	ISO 179/1eA
Flexural modulus (23°C)	4070	MPa	ISO 178
<b>Thermal properties</b>			
<b>ISO Data</b>			
Burning behav. at thickness h	HB	class	IEC 60695-11-10
<b>Other properties</b>			
<b>ISO Data</b>			
Density	1470	kg/m <sup>3</sup>	ISO 1183
<b>Characteristics</b>			
<b>Features</b>			
Copolymer			