



DURACon® TF-20			
POM			
Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Strength	45	MPa	ISO 527-1/-2
Nominal strain at break	50	%	ISO 527-1/-2
Charpy notched impact strength (+23°C)	17	kJ/m <sup>2</sup>	ISO 179/1eA
Flexural modulus (23°C)	1550	MPa	ISO 178
<b>Characteristics</b>			
<b>Special Characteristics</b>	<b>Features</b>		
High impact or impact modified	Copolymer		