


Tarnoform® 300 MW4

POM-MD20

Grupa Azoty S.A.

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	5.5	cm³/10min	ISO 1133
Temperature	190	°C	ISO 1133
Load	2.16	kg	ISO 1133
Melt flow index, MFI	7	g/10min	ISO 1133
MFI temperature	190	°C	ISO 1133
MFI load	2.16	kg	ISO 1133
Mechanical properties			
ISO Data			
Tensile Modulus	6400	MPa	ISO 527-1/-2
Tensile Strength	70	MPa	ISO 527-1/-2
Strain at break	5.5	%	ISO 527-1/-2
Charpy impact strength (+23°C)	40	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	4	kJ/m²	ISO 179/1eA
Flexural modulus (23°C)	5900	MPa	ISO 178
Izod Impact notched, 23°C	4	kJ/m²	ISO 180/1A
Ball indentation hardness	180	MPa	ISO 2039-1
Thermal properties			
ISO Data			
Melting temperature (10°C/min)	167	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	145	°C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	155	°C	ISO 306
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.2	mm	IEC 60695-11-10
Electrical properties			
ISO Data			
Relative permittivity, 1MHz	4	-	IEC 60250
Dissipation factor, 1MHz	95	E-4	IEC 60250
Volume resistivity	1E12	Ohm*m	IEC 60093
Surface resistivity	1E14	Ohm	IEC 60093
Electric strength	25	kV/mm	IEC 60243-1
Comparative tracking index	600	-	IEC 60112
Other properties			
ISO Data			
Humidity absorption	0.2	%	Sim. to ISO 62
Density	1550	kg/m³	ISO 1183
Characteristics			
Processing		Features	
Injection Molding		Copolymer	
Delivery form			
Granules, Black, Natural Color			