



Tarnoform® 300UV				
POM				
Rheological properties		Value	Unit	Test Standard
<b>ISO Data</b>				
Melt volume-flow rate, MVR	7	cm <sup>3</sup> /10min	ISO 1133	
Temperature	190	°C	ISO 1133	
Load	2.16	kg	ISO 1133	
Molding shrinkage, parallel	2.0	%	ISO 294-4, 2577	
Melt flow index, MFI	8	g/10min	ISO 1133	
MFI temperature	190	°C	ISO 1133	
MFI load	2.16	kg	ISO 1133	
<b>Mechanical properties</b>				
<b>ISO Data</b>		Value	Unit	Test Standard
Tensile Modulus	2600	MPa	ISO 527-1/-2	
Yield stress	55	MPa	ISO 527-1/-2	
Yield strain	9.5	%	ISO 527-1/-2	
Strain at break	45	%	ISO 527-1/-2	
Charpy impact strength (+23°C)	150	kJ/m <sup>2</sup>	ISO 179/1eU	
Charpy notched impact strength (+23°C)	5.5	kJ/m <sup>2</sup>	ISO 179/1eA	
Flexural modulus (23°C)	2300	MPa	ISO 178	
Izod Impact notched, 23°C	6	kJ/m <sup>2</sup>	ISO 180/1A	
Ball indentation hardness	145	MPa	ISO 2039-1	
<b>Thermal properties</b>				
<b>ISO Data</b>		Value	Unit	Test Standard
Melting temperature (10°C/min)	167	°C	ISO 11357-1/-3	
Temp. of deflection under load (1.80 MPa)	105	°C	ISO 75-1/-2	
Vicat softening temperature, 50°C/h 50N	145	°C	ISO 306	
Coeff. of linear therm. expansion, parallel	110	E-6/K	ISO 11359-1/-2	
Burning behav. at thickness h	HB	class	IEC 60695-11-10	
Thickness tested	3.2	mm	IEC 60695-11-10	
<b>Electrical properties</b>				
<b>ISO Data</b>		Value	Unit	Test Standard
Relative permittivity, 1MHz	3.9	-	IEC 60250	
Dissipation factor, 1MHz	85	E-4	IEC 60250	
Volume resistivity	1E13	Ohm*m	IEC 60093	
Surface resistivity	1E14	Ohm	IEC 60093	
Electric strength	25	kV/mm	IEC 60243-1	
Comparative tracking index	600	-	IEC 60112	
<b>Other properties</b>				
<b>ISO Data</b>		Value	Unit	Test Standard
Humidity absorption	0.2	%	Sim. to ISO 62	
Density	1410	kg/m <sup>3</sup>	ISO 1183	
<b>Characteristics</b>				
<b>Processing</b>		<b>Features</b>		
Injection Molding		Copolymer		
<b>Delivery form</b>		<b>Chemical Resistance</b>		
Granules, Black		General Chemical Resistance		

**Tarnoform® 300UV**

POM

Grupa Azoty S.A.

**Special Characteristics**

Light stabilized or stable to light, U.V. stabilized or stable to weather

**Applications**

Automotive