

Tarnoform® 500 GF2			
POM-GF10			
Grupa Azoty S.A.			
Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	11	cm ³ /10min	ISO 1133
Temperature	190	°C	ISO 1133
Load	2.16	kg	ISO 1133
Molding shrinkage, parallel	1.6	%	ISO 294-4, 2577
Molding shrinkage, normal	1.7	%	ISO 294-4, 2577
Melt flow index, MFI	13	g/10min	ISO 1133
MFI temperature	190	°C	ISO 1133
MFI load	2.16	kg	ISO 1133
Mechanical properties			
ISO Data			
Tensile Modulus	5100	MPa	ISO 527-1/-2
Tensile Strength	85	MPa	ISO 527-1/-2
Strain at break	2.5	%	ISO 527-1/-2
Charpy impact strength (+23°C)	30	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	3.5	kJ/m ²	ISO 179/1eA
Flexural modulus (23°C)	4500	MPa	ISO 178
Izod Impact notched, 23°C	4.5	kJ/m ²	ISO 180/1A
Ball indentation hardness	190	MPa	ISO 2039-1
Thermal properties			
ISO Data			
Melting temperature (10°C/min)	167	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	160	°C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	155	°C	ISO 306
Coeff. of linear therm. expansion, parallel	60	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	90	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.2	mm	IEC 60695-11-10
Electrical properties			
ISO Data			
Relative permittivity, 1MHz	4.2	-	IEC 60250
Dissipation factor, 1MHz	95	E-4	IEC 60250
Volume resistivity	1E12	Ohm*m	IEC 60093
Surface resistivity	1E13	Ohm	IEC 60093
Electric strength	25	kV/mm	IEC 60243-1
Comparative tracking index	600	-	IEC 60112
Other properties			
ISO Data			
Water absorption	0.8	%	Sim. to ISO 62
Humidity absorption	0.17	%	Sim. to ISO 62
Density	1490	kg/m ³	ISO 1183
Characteristics			
Processing		Features	
Injection Molding		Copolymer	

Tarnoform® 500 GF2

POM-GF10

Grupa Azoty S.A.

Delivery form

Granules, Black, Natural Color

Applications

Automotive, Building Construction, Electrical and Electronical