


Sarlink® 4190 - Shore 90 A

TPV

Teknor Apex Co.

Product Texts

Property	Value	Unit	Standard
Hardness Shore (5 sec delay, Extruded sample)	86A	-	ISO 868
Hardness Shore (5 sec delay, Injection molded sample)	90A	-	ISO 868
Tensile strength at break (Cross direction)	14.5	MPa	ISO 37
Modulus at 100% elongation (Cross direction)	6.7	MPa	ISO 37
Elongation at break (Cross direction)	650	%	ISO 37
Compression set (70h/125°C)	72	%	ISO 815
Hot air aging (168h/150°C, Cross Direction)			ISO 188
Change in hardness	3	points	
Retention tensile strength at break	92	%	
Retention modulus at 100% elongation	110	%	
Retention elongation at break	83	%	
Hot air aging (1000h/135°C, Cross Direction)			ISO 188
Change in hardness	3	points	
Retention tensile strength at break	89	%	
Retention modulus at 100% elongation	115	%	
Retention elongation at break	84	%	
Volume swell (70h/125°C in IRM 903 oil)	54	%	ISO 1817
Rheology (Apparent Shear Viscosity @ 206 1/s, 200°C)	340	Pa.s	ISO 11443 Capillary

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Stress at 100% elongation	10.2	MPa	ISO 527-1/-2
Strain at break TPE	>300	%	ISO 527-1/-2
Stress at break TPE	13.6	MPa	ISO 527-1/-2
Compression Set under constant strain, 23°C	36	%	ISO 815
Compression Set under constant strain, 70°C	48	%	ISO 815
Tear strength	71	kN/m	ISO 34-1

Other properties	Value	Unit	Test Standard
ISO Data			
Density	950	kg/m³	ISO 1183

Characteristics
Processing

Injection Molding, Other Extrusion, Blow Molding

Chemical Resistance

General Chemical Resistance