

Sarlink® 4775B40 - Shore 76 A

TPV

Teknor Apex Co.

Product Texts

Property	Value	Unit	Standard
Hardness Shore (5 sec delay, Extruded sample)	74A	-	ISO 868
Hardness Shore (5 sec delay, Injection molded sample)	76A	-	ISO 868
Tensile strength at break (Cross direction)	6.6	MPa	ISO 37
Modulus at 100% elongation (Cross direction)	3.1	MPa	ISO 37
Elongation at break (Cross direction)	490	%	ISO 37
Compression set (70h/125°C)	52	%	ISO 815
Hot air aging (168h/150°C, Cross Direction)			ISO 188
Change in hardness	1	points	
Retention tensile strength at break	78	%	
Retention modulus at 100% elongation	102	%	
Retention elongation at break	71	%	
Hot air aging (1000h/135°C, Cross Direction)			ISO 188
Change in hardness	3	points	
Retention tensile strength at break	88	%	
Retention modulus at 100% elongation	105	%	
Retention elongation at break	84	%	
Volume swell (70h/125°C in IRM 903 oil)	74	%	ISO 1817
Rheology (Apparent Shear Viscosity @ 206 1/s, 200°C)	220	Pa.s	ISO 11443 Capillary

Mechanical properties**Value****Unit****Test Standard****ISO Data**

Stress at 100% elongation	3.5	MPa	ISO 527-1/-2
Strain at break TPE	>300	%	ISO 527-1/-2
Stress at break TPE	6	MPa	ISO 527-1/-2
Compression Set under constant strain, 23°C	24	%	ISO 815
Compression Set under constant strain, 70°C	36	%	ISO 815
Tear strength	33	kN/m	ISO 34-1

Other properties**Value****Unit****Test Standard****ISO Data**

Density	910	kg/m³	ISO 1183
---------	-----	-------	----------

Characteristics**Processing**

Injection Molding

Special Characteristics

U.V. stabilized or stable to weather

Delivery form

Black

Chemical Resistance

General Chemical Resistance