


Sarlink® 6135N - Shore 36 A

TPV

Teknor Apex Co.

Product Texts

Property	Value	Unit	Standard
Hardness Shore (5 sec delay, Extruded sample)	32A	-	ISO 868
Hardness Shore (5 sec delay, Injection molded sample)	36A	-	ISO 868
Tensile strength at break (Cross direction)	2.7	MPa	ISO 37
Modulus at 100% elongation (Cross direction)	0.8	MPa	ISO 37
Elongation at break (Cross direction)	555	%	ISO 37
Compression set (70h/125°C)	43	%	ISO 815
Rheology (Apparent Shear Viscosity @ 206 1/s, 200°C)	195	Pa.s	ISO 11443 Capillary

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Stress at 100% elongation	1.1	MPa	ISO 527-1/-2
Strain at break TPE	>300	%	ISO 527-1/-2
Stress at break TPE	2.3	MPa	ISO 527-1/-2
Compression Set under constant strain, 23°C	23	%	ISO 815
Compression Set under constant strain, 70°C	30	%	ISO 815
Tear strength	10.5	kN/m	ISO 34-1

Other properties	Value	Unit	Test Standard
ISO Data			
Density	888	kg/m³	ISO 1183

Characteristics
Processing

Injection Molding

Features

Low Fogging

Delivery form

Natural Color

Chemical Resistance

General Chemical Resistance

Special Characteristics

Heat stabilized or stable to heat

Applications

Automotive, Sports Equipment