



DIAMOND POLYMERS, INC.

ASA Weatherable Polymers
Injection Molding Grade

ASA S124
Medium Modulus

PROPERTIES	ASTM METHOD	UNITS ENGLISH METRIC	
PHYSICAL			
Melt Flow Rate - Procedure A 200° C/5.0 kg 230° C/3.8 kg 220°C/10 kg	D-1238	g/10 min	1.8 5.4 26.0
Specific Gravity	D-792		1.07
Mold Shrinkage	D-955	in/in cm/cm	0.004-0.008 0.004-0.008
IMPACT			
Izod Impact, notched 0.125" bar, 23° C (73° F)	D-256	ft-lb/in J/m	1.9 101.5
FLEXURAL			
Flexural Modulus, tangent chs 0.05 in/min	D-790	psi MPa	339,000 2336
TENSILE			
Tensile Yield Strength, chs 2 in/min	D-638	psi MPa	6,653 45.8
THERMAL			
Heat Deflection Temperature 0.125" bar @ 264 psi Unannealed/Conditioned 40 hours @ 23° C (73° F)	D-648	°F °C	180 82
Vicat Softening Point 0.125" bar/wt 1000g	D-1525	°F °C	228 109

EAP/02-05

The information contained herein is provided for general reference purposes only. Diamond Polymers Inc. makes no guarantee or warranty and does not assume liability with respect to the accuracy or completeness of the information presented, or the product results in any specific instance and hereby expressly disclaims any implied warranties of suitability or fitness for a particular purpose or any other warranties or representations whatsoever expressed or implied. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of patent.