

Nilamid B3 H G5 Processing guide



Nilit Plastics Division

INTEGRATED - PROFESSIONAL - COMMITTED - PARTNERS - RELIABLE - SOLUTIONS - RESEARCH - COOPERATION - SMART - INNOVATIVE - CHALLENGES - CONSISTENT - CREATIVENESS - FRIENDS



-IONet-

PROCESSING GUIDE NILAMID B3 H G5

Nilamid B3 H G5 is a standard purpose, 25% glass fibre reinforced PA6. This product combines good overall mechanical and thermal performance with ease of processing.

Before processing this material, please read the safety data sheet and this processing guide carefully.

Nilamid B3 H G5 is an easy to mould material, which can be processed on most standard injection moulding equipment.

Pre-drying

Nilamid B3 H G5 is hygroscopic and moisture sensitive, so pre-drying is recommended as a matter of rule. Material that is not pre-dried to a moisture level below 0.1% will degrade, causing surface defects, parts that are out of dimension and brittle parts. It is recommended to dry material for 4 hours at 80 °C to 85 °C in a desiccant dryer with more than one desiccant element.

A few tips to ensure proper operation of the dryer:

- Ensure the thermocouple that regulates the temperature is placed immediately before the entry of the air into the dryer. There can be a significant temperature drop in the air-conveyance system!
- The temperature of the air going out of the dryer silo should not be more than 30 °C lower than the air entering the system. If this is the case, you have insufficient air capacity.
- From time to time, monitor the dew point of the dry air to ensure the desiccant elements are functioning properly.

Often, less air runs through the very bottom part of a dryer silo. Therefore, it is recommended that you take the material out of the bottom of the dryer and feed it back into the top when you start up your process.

Moulding temperatures

For Nilamid B3 H G5, the melt temperature must be kept below 310 °C. Any higher temperature will cause rapid degradation, which may result in brittle parts.

The following barrel settings are recommended:

Material	Zone 1 (hopper)	Zone 2	Zone 3	Zone 4 (Nozzle)
Nilamid B3 H G5	240-270 °C	240-270 °C	245-285 °C	245-290 °C

The recommended melt temperature ranges from 245 to 280°C.

PROCESSING GUIDE NILAMID B3 H G5

Tool temperature

Mould temperature is always a compromise. On the one hand, tool temperature should be as high as possible to give optimum crystallization and dimensional, optimal surface finish and optimal mechanical performance. On the other hand, lower tool temperature can significantly cut cycle time. For Nilamid B3 H G5, 80 °C should be maintained as a minimum, for reinforced grades values of 90 to 110 °C are preferred.

Pressure and speed

Injection pressure should generally be around 70 to 100 MPa; this results in a minimum clamping force of the moulding machine in tonnes of 0.7 times the projected surface area in cm².

Holding pressure is generally in the area of 90 MPa.

For Nilamid B3 H G5, the screw speed should be kept low, a rough indication is as follows:

Screw Diameter (mm)	Maximum rpm
20	150
30	100
40	70
50	60
60	50
70	40
80	35
>80	30

Back pressure should be kept to a practical minimum

Use of regrind

Parts have been moulded successfully with regrind levels of up to 30%. When regrind is used, observe these simple rules:

- Use a constant ratio of regrind and virgin material. When a material has been processed once, its viscosity and fibre length have been decreased. Using varying ratios of regrind can lead to variations in dimensions, mechanical performance and processing characteristics.
- Either feed the regrind straight back into the machine, or pre-dry the regrind before usage.
- Store regrind in a dry, clean place to avoid contamination and excess moisture.
- Ensure sharp cutting blades to keep dust generation to a minimum; cut glass fibre reinforced material when it is still hot.



PROCESSING GUIDE NILAMID B3 H G5

Special instructions

- Always pre-dry the material and any regrind that is not fed back immediately into the machine to below 0.1% moisture
- Keep the melt temperature below 310 °C, particularly in areas where long residence times may occur, like hot runners
- When the machine is stopped, purge with PE or a suitable purging compounds. Do not leave the material standing for longer than 30 minutes without purging

Contacts:

Americas:

Nilit America Corp.
Mr. Moshe Nitzan
Tel: +1 8606520007
Fax: +1 8606520880
e-mail: Moshen@nilit.co.il

Benelux

E&B Polymers
Tel: +31 (0)76 5300065
Fax: +31 (0)76 5206026
e-mail: ebpolymers@eb-cc.com

France

Snetor Distribution
Tel: +33 (0) 149048888
Fax: +33 (0) 149048898
e-mail: ppopelin@snetor.fr

Germany:

Jörg Konrad
Tel: +49 (0)6044 951630
Fax: +49 (0)6044 951631
e-mail: J.Konrad@nilit.co.il

Fred Panhuizen

Tel: +31 (0)13 5833807
Fax: +31 (0)13 5833807
e-mail: fred@nilit.co.il

Italy:

Euronil S.p.A.
Tel: +39 0293179702
Fax: +39 0293179733
e-mail: euronil@nilit.co.il

Scandinavia:

Mape Plastics AB
Tel: +46 (0)33 417030
Fax: +46 (0)33 417035
e-mail: info@mapeplastics.se

United Kingdom:

Hellyar Plastics
Tel: +44 (0)1227813200
Fax: +44 (0)1227792203
e-mail: info@hellyar.co.uk

Other countries:

Euronil S.p.A.
Mrs Barbara Giunta
Tel: +39 0293179702
Fax: +39 0293179733
e-mail: Barbara.Giunta@nilit.co.il