

RILSAN® BZM 30 BLACK TL

PA11,MHL,18-070,GF30

Rilsan® BZM 30 BLACK TL is a fiberglass reinforced polyamide 11 produced from a renewable source. This black grade is designed for injection molding.

The percentage of renewable carbon according to ASTM D 6866 (calculated) is **>95%**.

MAIN CHARACTERISTICS

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	7 / *	cm ³ /10min	ISO 1133
Temperature	235 / *	°C	-
Load	5 / *	kg	-
MECHANICAL PROPERTIES			
Tensile Modulus	- / 6900	MPa	ISO 527-1/-2
Stress at Break	- / 110	MPa	ISO 527-1/-2
Strain at Break	- / 6	%	ISO 527-1/-2
Shore D Hardness, 15s	74 / *	-	ISO 7619-1
Charpy Impact Strength, +23°C	- / 74	kJ/m ²	ISO 179/1eU
Charpy Impact Strength, -30°C	- / 83	kJ/m ²	ISO 179/1eU
Charpy Notched Impact Strength, +23°C	- / 20	kJ/m ²	ISO 179/1eA
Charpy Notched Impact Strength, -30°C	- / 11	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	189 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES			
Water Absorption	1.3 / *	%	Sim. to ISO 62
Density	1250 / 1250	kg/m ³	ISO 1183
%Bio-Based	95	-	ASTM D6866

MAIN APPLICATIONS:

- Quick connectors

PACKAGING:

This grade is delivered dried in sealed packaging (25 kg bags) ready to be processed.

SHELF LIFE:

Two years from the delivery. For any use above this limit, please refer to our technical services.

Processing conditions:

- Typical melt temperature (Min / Recommended / Max) : 250°C / 270°C / 290°C.
- Mold temperature : 40 - 90°C

RILSAN® BZM 30 BLACK TL

- Drying time and temperature (only necessary for bags opened for more than two hours) : 4-6 hours at 80-90°C.

PROCESSING

Injection Molding

DELIVERY FORM

Pellets

SPECIAL CHARACTERISTICS

Bio-Based, Heat Stabilized, Light Stabilized

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Rilsan® is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

rilsan.com

RILSAN®
BY ARKEMA

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790
SDC/11-2018