

FZ-6600-B2

- **Product Summary:** FZ-6600-B2 is a glass fiber and mineral filled linear PPS compound with excellent mechanical and high flow properties.
- **Color:** Natural (off white)

Engineering Properties of FZ-6600-B2

Properties	Test Method	Unit	FZ-6600-B2
General Information			GF/Filler High flow
Physical			
Density	ISO 1183	g/cm ³	1.89
Water absorption, 23°C/24Hrs.	ISO 62	%	0.01
Mold shrinkage ^a	ISO 294-4	%	0.2/0.7
Mechanical			
Tensile strength	ISO 527-1,2	MPa	160
Tensile modulus	ISO 527-1,2	GPa	19.5
Tensile strain at break	ISO 527-1,2	%	1.3
Flexural strength	ISO 178	MPa	240
Flexural modulus	ISO 178	GPa	19.0
Flexural strain at break	ISO 178	%	1.5
Charpy impact strength, notched	ISO 179/1eA	kJ/m ²	9
unnotched	ISO 179/1eU	kJ/m ²	30
Co-eff. of friction ^b , static/dynamic	-	-	0.35/0.35
Thermal			
Heat deflection temperature, 1.80MPa	ISO 75-1,2	°C	275
Co-eff. of linear thermal expansion ^a , -50~50 °C	ISO 11359-2	x 10 ⁻⁵ /K	1.5/2.5
Co-eff. of linear thermal expansion ^a , 100~200 °C	ISO 11359-2	x 10 ⁻⁵ /K	1.5/7.0
Flammability ^c /thickness (mm)	UL-94	-	V-0/0.73
Electrical			
Dielectric strength, t=1.0mm	IEC 60243-1	kV/mm	22
Dielectric constant, 1MHz	IEC 60250	-	5
Dissipation factor, 1MHz	IEC 60250	-	0.002
Comparative Tracking Index (CTI)	IEC 60112	V	175
Volume resistivity	IEC 60093	Ω·cm	10 ¹⁶
Molding Condition			
Cylinder temperature	-	°C	300-340
Mold temperature	-	°C	130-150

a: Flow direction/Transverse direction

b: P=150kPa, V=0.3m/s, PPS vs. carbon steel

c: UL file No. E53829