



HIVAL® 2535

Ashland Inc. - Polypropylene Random Copolymer

Wednesday, 03 November 2010

General Information

General

Material Status	• Commercial: Active
Availability	• North America
Features	• High Clarity
Uses	• General Purpose
Forms	• Pellets

ASTM and ISO Properties¹

	Nominal Value	Unit	Test Method
Physical			
Density	0.900	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	35	g/10 min	ASTM D1238
Mechanical			
Tensile Strength (Yield)	3900	psi	ASTM D638
Flexural Modulus	130000	psi	ASTM D790
Impact			
Notched Izod Impact	1.1	ft-lb/in	ASTM D256

Notes

¹ Typical properties: these are not to be construed as specifications.



Copyright © 2010 - IDES - The Plastics Web ®

The information presented on this data sheet was acquired by IDES from the producer of the material. IDES makes substantial efforts to assure the accuracy of this data. However, IDES assumes no responsibility for the data values and strongly encourages that upon final material selection, data points are validated with the material supplier.

Page: 1 of 1