

Nilamid A3 H7 G7 natural



PA66, 35% glass fibre reinforced, high heat aging resistant

	Properties	Conditions	Unit	Standard	Values
Physical	Density	23°C	g/cm³	ISO 1183, ASTM D792	1,41
	Mould shrinkage (parallel)	23°C	%	Euronil	0,3
	Mould shrinkage (normal)	23°C	%	Euronil	0,4
	Moisture absorption in water	23°C - 24h	%	ISO 62 (based on)	0,6
		23°C saturation	%	ISO 62 (based on)	4,5
Mechanical	Notched Izod Impact Strength	23°C	KJ/m²	ISO 180/1A	11
		-30°C	KJ/m²	ISO 180/1A	—
	Unnotched Charpy Impact Strength	23°C	KJ/m²	ISO 179	55
		-30°C	KJ/m²	ISO 179	—
	Notched Charpy Impact Strength	23°C	KJ/m²	ISO 179	12
		-30°C	KJ/m²	ISO 179	—
	Tensile yield stress	23°C	MPa	ISO 527, ASTM D638	180
	Tensile modulus	23°C	MPa	ISO 527, ASTM D638	—
	Yield strain	23°C	%	ISO 527, ASTM D638	—
	Strain at break	23°C	%	ISO 527, ASTM D638	2,0
	Flexural yield strength	23°C	MPa	ISO 178, ASTM D790	280
		90°C	MPa	ISO 178, ASTM D790	—
	Flexural Modulus	23°C	MPa	ISO 178, ASTM D790	10000
		90°C	MPa	ISO 178, ASTM D790	6500
Thermal	VICAT - softening temperature	9.8 N	°C	ISO 306, ASTM D1525	258
		49 N	°C	ISO 306, ASTM D1525	253
	HDT - temperature of deflection under load	0.45 N/mm²	°C	ISO 75, ASTM D 648	260
		1.82 N/mm²	°C	ISO 75, ASTM D 648	252
	Heat resistance - Ball test	125°C		IEC 309	OK
		165°C		IEC 309	OK
	Continuous service temperature	20000 h	°C	IEC 216	140
Electrical	Dielectric Strength	2 mm	KV/mm	ASTM D149	21
	CTI - Comparative Tracking Index	3.2 mm, sol. A	V	IEC 112, UL 746A	450
		3.2 mm, sol. B	V	IEC 112, UL 746A	325M
Flame behaviour	Oxygen Index		%	ASTM D2863	25
	Flammability rating	3.2 (1.6) mm		UL 94	HB
		0.8 (0.4) mm		UL 94	HB
	Needle test	2.0 (1.0) mm		IEC 695-2-2	—
	Glow wire Flammability Index	3.2 (0.8) mm	°C	IEC 695-2-12	650 (650)
	Glow wire Ignition Temperature	3.2 (0.8) mm	°C	IEC 695-2-13	—
	Flammability rating	355x100x1 mm		FMVSS No.302	—

Technical Data Sheet

The information in this datasheet is given in good faith but without warranty. These data do not release you from the obligation to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you are beyond our control and, therefore, entirely your own responsibility. Nilamid is a registered name of Euronil and is registered throughout Europe. The mark is not registered in the US and no product are sold by Euronil under this name in the US. rev. 01/07/03

