

Polynil P50 N natural



Plastics Division

PA66, unfilled, nucleated, 2.7 viscosity

	Properties	Conditions	Unit	Standard	Values
Physical	Density	23°C	g/cm ³	ISO 1183, ASTM D792	1,14
	Mould shrinkage (parallel)	23°C	%	Euronil	1,1
	Mould shrinkage (normal)	23°C	%	Euronil	—
	Moisture absorption in water	23°C - 24h	%	ISO 62 (based on)	1,5
		23°C saturation	%	ISO 62 (based on)	8,5
Mechanical	Notched Izod Impact Strength	23°C	KJ/m ²	ISO 180/1A	5,5
		-30°C	KJ/m ²	ISO 180/1A	—
	Unnotched Charpy Impact Strength	23°C	KJ/m ²	ISO 179	—
		-30°C	KJ/m ²	ISO 179	—
	Notched Charpy Impact Strength	23°C	KJ/m ²	ISO 179	—
		-30°C	KJ/m ²	ISO 179	—
	Tensile yield stress	23°C	MPa	ISO 527, ASTM D638	90
	Tensile modulus	23°C	MPa	ISO 527, ASTM D638	3400
	Yield strain	23°C	%	ISO 527, ASTM D638	—
	Strain at break	23°C	%	ISO 527, ASTM D638	26
	Flexural yield strength	23°C	MPa	ISO 178, ASTM D790	123
		90°C	MPa	ISO 178, ASTM D790	—
	Flexural Modulus	23°C	MPa	ISO 178, ASTM D790	2900
		90°C	MPa	ISO 178, ASTM D790	—
Thermal	VICAT - softening temperature	9.8 N	°C	ISO 306, ASTM D1525	—
		49 N	°C	ISO 306, ASTM D1525	—
	HDT - temperature of deflection under load	0.45 N/mm ²	°C	ISO 75, ASTM D 648	238
		1.82 N/mm ²	°C	ISO 75, ASTM D 648	71
	Heat resistance - Ball test	125°C		IEC 309	—
		165°C		IEC 309	—
	Continuous service temperature	20000 h	°C	IEC 216	—
Electrical	Dielectric Strength	2 mm	KV/mm	ASTM D149	—
	CTI - Comparative Tracking Index	3.2 mm, sol. A	V	IEC 112, UL 746A	—
		3.2 mm, sol. B	V	IEC 112, UL 746A	—
Flame behaviour	Oxygen Index		%	ASTM D2863	—
	Flammability rating	3.2 (1.6) mm		UL 94	V-2
		0.8 (0.4) mm		UL 94	V-2
	Needle test	2.0 (1.0) mm		IEC 695-2-2	—
	Glow wire Flammability Index	3.2 (0.8) mm	°C	IEC 695-2-12	—
	Glow wire Ignition Temperature	3.2 (0.8) mm	°C	IEC 695-2-13	—
	Flammability rating	355x100x1 mm		FMVSS No.302	—

Technical Data Sheet

The information in this datasheet is given in good faith but without warranty. These data do not release you from the obligation to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you are beyond our control and, therefore, entirely your own responsibility. rev. 01/04/03