

Polyether bloc amide PEBAX® **MX 1205 SP 01** is a thermoplastic elastomer made of flexible polyether and rigid polyamide. This SP grade has been developed to be heat and UV resistant, with improved properties compared to SN grades.

Main Characteristics	Value	Unit	Test Method
Density	1.01	g/cm ³	ISO 1183
Water Absorption at Equilibrium at 20°C and 50 % RH	0.4	%	ISO 62
Water Absorption at Saturation 24 h in water at 23°C	1.2	%	
Melting Point	147	°C	ISO 11357
Vicat Point Under 1 daN	111	°C	ISO 306
Hardness Shore (*) Instantaneous	46	Shore D	ISO 868
After 15 s	41	Shore D	
Tensile Test (*) Stress at Break	42	MPa	ASTM D 638
Strain at Break	>550	%	
Flexural Modulus (*)	86	MPa	ISO 178
Charpy Impact unnotched 23°C	No break	kJ/m ²	ISO 179
unnotched -30°C	No break	kJ/m ²	
V-notched 23°C	No break	kJ/m ²	
V-notched -30°C	No break	kJ/m ²	

(*) Samples conditioned 15 days at 23°C - 50 % R.H.

Processing Conditions	Typical Values
Drying (*): Time / Temperature	4-6 hours / 60-70°C
Injection Temperature: Min / Recommended / Max	200°C / 240°C / 270°C
Extrusion Temperature: Min / Recommended / Max	210°C / 220°C / 230°C
Mold Temperature:	10-30°C

(*) Pebax® is delivered dried in sealed packaging ready to be processed. Drying is only necessary for bags opened for more than 2 hours.

DPT/TDS/53895/ April 2008

The information contained in this document is based on trials carried out by our Research Centres and data selected from the literature, but shall in no event be held to constitute or imply any warranty, undertaking, express or implied commitment from our part. Our formal specifications define the limit of our commitment. No liability whatsoever can be accepted by Arkema with regard to the handling, processing or use of the product or products concerned which must in all cases be employed in accordance with all relevant laws and/or regulations in force in the country or countries concerned.