

Polyether block amide **PEBAX® 2533 SD 01** is a thermoplastic elastomer made of flexible polyether and rigid polyamide. This SD grade is heat and UV stabilized and contains mould release additive.

Main Characteristics	Value	Unit	Test Method
Density	1.00	g/cm ³	ISO 1183
Water Absorption at Equilibrium at 20°C and 50 % RH	0.4	%	ISO 62
Water Absorption at Saturation 24 h in water at 23°C	1.2	%	
Melting Point	134	°C	ISO 11357
Vicat Point Under 1 daN	58	°C	ISO 306
Hardness Shore (*) Instantaneous	27	Shore D	ISO 868
After 15 s	22	Shore D	
Tensile Test (*) Stress at Break Strain at Break	32 >750	MPa %	ASTM D 638
Flexural Modulus (*)	12	MPa	ISO 178
Charpy Impact unnotched 23°C unnotched -30°C V-notched 23°C V-notched -30°C	No break No break No break No break	kJ/m ² kJ/m ² kJ/m ² kJ/m ²	ISO 179

(*) Samples conditioned 15 days at 23°C - 50 % R.H.

Processing Conditions	Typical Values
Drying (*): Time / Temperature	4-8 hours / 55-65°C
Injection Temperature: Min / Recommended / Max	180°C / 210°C / 240°C
Mold Temperature:	10-30°C

(*) Pebax® is delivered dried in sealed packaging ready to be processed. Drying is only necessary for bags opened for more than 2 hours.

DPT/TDS/10211/April 2008

The information contained in this document is based on trials carried out by our Research Centres and data selected from the literature, but shall in no event be held to constitute or imply any warranty, undertaking, express or implied commitment from our part. Our formal specifications define the limit of our commitment. No liability whatsoever can be accepted by Arkema with regard to the handling, processing or use of the product or products concerned which must in all cases be employed in accordance with all relevant laws and/or regulations in force in the country or countries concerned.