

Polyether block amide **PEBAX® MV 1074 SP 01** is a thermoplastic elastomer made of flexible polyether and rigid polyamide. MV 1074 SP 01 is an inherently dissipative polymer and can be dry blended or compounded with an isolative polymer to lower the surface resistivity. This SP grade has been developed to be heat and UV resistant, with improved properties compared to SN grades.

Main Characteristics	Value	Unit	Test Method
Density	1.07	g/cm ³	ISO 1183
Water Absorption at Equilibrium at 20°C and 50 % RH	1.4	%	ISO 62
Water Absorption at Saturation 24 h in water at 23°C	48	%	
Melting Point	158	°C	ISO 11357
Hardness Shore (*) Instantaneous	40	Shore D	ISO 868
Tensile Test (*) Stress at Break	30	MPa	ASTM D 638
Flexural Modulus (*)	700	MPa	ISO 178
Surface Resistivity (*)	3 10⁹	Ω / sq	IEC 60093
Volume Resistivity (*)	2.5 10⁹	Ω.cm	IEC 60093
Charge Decay Time	<1	sec	MIL B-81705

(*) Samples conditioned 15 days at 23°C - 50 % R.H.

DPT/TDS/57006/August 2008

The information contained in this document is based on trials carried out by our Research Centres and data selected from the literature, but shall in no event be held to constitute or imply any warranty, undertaking, express or implied commitment from our part. Our formal specifications define the limit of our commitment. No liability whatsoever can be accepted by Arkema with regard to the handling, processing or use of the product or products concerned which must in all cases be employed in accordance with all relevant laws and/or regulations in force in the country or countries concerned.