



Americas Styrenics EB6400

Americas Styrenics LLC - High Impact Polystyrene

Tuesday, November 5, 2019

General Information

General

Material Status	• Commercial: Active	
Availability	• North America	
Features	• Excellent Printability • Food Contact Acceptable	• High Heat Resistance • Low Temperature Toughness
Uses	• Decorative Displays • Packaging	• Screen Printing • Toys
Agency Ratings	• FDA 21 CFR 177.1640	
UL File Number	• E326906	
Forms	• Pellets	
Processing Method	• Extrusion	• Injection Molding

ASTM & ISO Properties¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.04		ASTM D792
Melt Mass-Flow Rate (200°C/5.0 kg)	3.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	4.0E-3 to 8.0E-3	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (Injection Molded)	218000	psi	ASTM D638
Tensile Strength (Injection Molded)	2900	psi	ASTM D638
Tensile Strength (Break, Injection Molded)	2900	psi	ASTM D638
Tensile Elongation (Break, Injection Molded)	75	%	ASTM D638
Flexural Modulus (Injection Molded)	218000	psi	ASTM D790
Flexural Strength (Injection Molded)	4350	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
73°F, Compression Molded	1.6	ft-lb/in	
73°F, Injection Molded	2.2	ft-lb/in	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	100		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	190	°F	ASTM D648
Deflection Temperature Under Load			ASTM D648
264 psi, Unannealed	174	°F	
Vicat Softening Temperature	213	°F	ASTM D1525
CLTE - Flow	5.0E-5	in/in/°F	ASTM D696

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	424 to 480	°F
Middle Temperature	424 to 480	°F
Front Temperature	390 to 415	°F
Nozzle Temperature	415 to 469	°F

Americas Styrenics EB6400

Americas Styrenics LLC - High Impact Polystyrene

Injection	Nominal Value	Unit
Mold Temperature	60 to 150	°F
Injection Rate	Fast	
Back Pressure	29.0 to 174	psi
Cushion	0.250	in
Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	351 to 379	°F
Cylinder Zone 2 Temp.	360 to 399	°F
Cylinder Zone 3 Temp.	370 to 410	°F
Cylinder Zone 4 Temp.	390 to 421	°F
Cylinder Zone 5 Temp.	399 to 430	°F
Adapter Temperature	379 to 450	°F
Melt Temperature	379 to 450	°F
Die Temperature	390 to 450	°F

Extrusion Notes

Zone 6 Temperature: 204 to 221°C
Melt Pump, Pipes, Screen Changer Temperature: 193 to 232°C
Polish Rolls Temperature: 66 to 104°C
Head Pressure: 10 to 21 MPa

Notes

¹ Typical properties: these are not to be construed as specifications.