



Celcon® LW25-S2

Celanese Corporation - Acetal (POM) Copolymer

Saturday, November 2, 2019

General Information

Product Description

Celcon® LW25-S2 acetal copolymer is a low flow, improved toughness product formulated with a low level of silicone to reduce friction and improved wear resistance.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
Additive	• Silicone Lubricant		
Features	• Good Toughness	• Lubricated	• Wear Resistant
RoHS Compliance	• Contact Manufacturer		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.38	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	2.10	cm ³ /10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	341000	psi	ISO 527-2/1A
Tensile Stress (Yield)	7830	psi	ISO 527-2/1A/50
Tensile Strain (Yield)	20	%	ISO 527-2/1A/50
Flexural Modulus (73°F)	334000	psi	ISO 178
Flexural Stress (3.5% Strain)	9430	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	4.3	ft·lb/in ²	ISO 179/1eA
Notched Izod Impact Strength (73°F)	4.3	ft·lb/in ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (264 psi, Unannealed)	194	°F	ISO 75-2/A
Melting Temperature ²	331	°F	ISO 11357-3
CLTE - Flow	6.1E-5	in/in/°F	ISO 11359-2
CLTE - Transverse	6.1E-5	in/in/°F	ISO 11359-2

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	212 to 248	°F
Drying Time	3.0 to 4.0	hr
Rear Temperature	338 to 356	°F
Middle Temperature	356 to 374	°F
Front Temperature	356 to 374	°F
Nozzle Temperature	374 to 392	°F
Processing (Melt) Temp	356 to 392	°F
Mold Temperature	176 to 248	°F
Injection Rate	Slow	
Back Pressure	< 580	psi

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

Celcon® LW25-S2

Celanese Corporation - Acetal (POM) Copolymer

Injection Notes

Zone4 temperature: 190 to 200°C

Hot runner temperature: 180 to 200°C

Notes

¹ Typical properties: these are not to be construed as specifications.

² 10°C/min