



Celcon® MR270B

Celanese Corporation - Acetal (POM) Copolymer

Sunday, November 3, 2019

General Information

Product Description

Celcon® MR270B is a high flow specialty media resistant grade developed for improved bleach resistance.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
Features	• High Flow		
RoHS Compliance	• Contact Manufacturer		

ASTM & ISO Properties ¹

	Nominal Value	Unit	Test Method
Physical			
Density	1.41	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	24	cm ³ /10min	ISO 1133
Mechanical			
Tensile Modulus	399000	psi	ISO 527-2/1A
Tensile Stress (Yield)	9570	psi	ISO 527-2/1A/50
Tensile Strain (Yield)	7.0	%	ISO 527-2/1A/50
Flexural Modulus (73°F)	406000	psi	ISO 178
Flexural Stress (3.5% Strain)	10900	psi	ISO 178
Impact			
Charpy Notched Impact Strength			ISO 179/1eA
-22°F	2.4	ft·lb/in ²	
73°F	2.4	ft·lb/in ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F	45	ft·lb/in ²	
73°F	48	ft·lb/in ²	
Notched Izod Impact Strength (73°F)	2.6	ft·lb/in ²	ISO 180/1A
Thermal			
Heat Deflection Temperature (264 psi, Unannealed)	212	°F	ISO 75-2/A
Melting Temperature ²	331	°F	ISO 11357-3

Processing Information

	Nominal Value	Unit
Injection		
Drying Temperature	212 to 248	°F
Drying Time	3.0 to 4.0	hr
Rear Temperature	338 to 356	°F
Middle Temperature	356 to 374	°F
Front Temperature	356 to 374	°F
Nozzle Temperature	356 to 392	°F
Processing (Melt) Temp	356 to 392	°F
Mold Temperature	176 to 248	°F
Injection Rate	Slow-Moderate	
Back Pressure	< 580	psi

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

Celcon® MR270B

Celanese Corporation - Acetal (POM) Copolymer

Injection Notes

Zone4 temperature: 180 to 200°C

Hot runner temperature: 180 to 200°C

Notes

¹ Typical properties: these are not to be construed as specifications.

² 10°C/min