



Celstran® POM-GF35-04 AF3001

Celanese Corporation - Acetal (POM) Copolymer

Sunday, November 3, 2019

General Information

Product Description

Material code according to ISO 1043-1: POM Acetal copolymer reinforced with 35 weight percent long glass fibers. The fibers are chemically coupled to the POM matrix. The pellets are cylindrical and normally as well as the embedded fibers 10 mm long. Parts molded of CELSTRAN have outstanding mechanical properties such as high strength and stiffness combined with high heat deflection. The notched impact strength is increased at elevated and low temperatures due to the fiber skeleton built in the parts. The long fiber reinforcement reduces creep significantly. The very isotropic shrinkage in the molded parts minimizes the warpage. Complex parts can be manufactured with high reproducibility by injection molding. Application field: Functional/structural parts for automotive

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Filler / Reinforcement	• Long Glass Fiber, 35% Filler by Weight		
Features	• Chemically Coupled • Creep Resistant • Good Isotropy	• High Stiffness • High Strength • Low Temperature Impact Resistance	• Low Warpage
Uses	• Automotive Applications		
RoHS Compliance	• Contact Manufacturer		
Forms	• Pellets		
Processing Method	• Injection Molding		
Resin ID (ISO 1043)	• POM		

ASTM & ISO Properties ¹

	Nominal Value	Unit	Test Method
Physical			
Density	1.65	g/cm ³	ISO 1183
Mechanical			
Tensile Modulus	1.74E+6	psi	ISO 527-2/1A
Tensile Stress (Break)	26400	psi	ISO 527-2/1A/50
Tensile Strain (Break)	2.1	%	ISO 527-2/1A/5
Flexural Modulus (73°F)	1.58E+6	psi	ISO 178
Flexural Stress (73°F)	41300	psi	ISO 178
Impact			
Charpy Notched Impact Strength (73°F)	20	ft·lb/in ²	ISO 179/1eA

Processing Information

	Nominal Value	Unit
Injection		
Drying Temperature	176 to 194	°F
Drying Time	3.0	hr
Suggested Max Moisture	0.15	%
Rear Temperature	356 to 383	°F
Middle Temperature	374 to 392	°F
Front Temperature	383 to 401	°F
Nozzle Temperature	383 to 401	°F
Processing (Melt) Temp	383 to 401	°F
Mold Temperature	158 to 230	°F

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

Celstran® POM-GF35-04 AF3001

Celanese Corporation - Acetal (POM) Copolymer

Injection	Nominal Value	Unit
Injection Rate	Moderate	
Back Pressure	< 435	psi

Injection Notes

Feeding zone temperature: 20 to 50°C

Zone4 temperature: 195 to 205°C

Hot runner temperature: 195 to 205°C

Notes

¹ Typical properties: these are not to be construed as specifications.