



## Celstran® PP-GF50-0455 P10/10

Celanese Corporation - Polypropylene

Tuesday, November 5, 2019

### General Information

#### Product Description

Material code according to ISO 1043-1: PP Heat and light stabilized polypropylene reinforced with 50 weight percent long glass fibers. The product has low emissions. The fibers are chemically coupled to the polypropylene matrix. The pellets are cylindrical and normally as well as the embedded fibers 10 mm long. Parts molded of CELSTRAN have outstanding mechanical properties such as high strength and stiffness combined with high heat deflection. The notched impact strength is increased at elevated and low temperatures due to the fiber skeleton built in the parts. The long fiber reinforcement reduces creep significantly. The very isotropic shrinkage in the molded parts minimizes the warpage.

Complex parts can be manufactured with high reproducibility by injection molding. Application field: Functional/structural parts for automotive

#### General

|                        |                                                                                                                                                                                                      |
|------------------------|------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Material Status        | • Commercial: Active                                                                                                                                                                                 |
| Availability           | • Asia Pacific • Europe • North America                                                                                                                                                              |
| Filler / Reinforcement | • Long Glass Fiber, 50% Filler by Weight                                                                                                                                                             |
| Additive               | • Heat Stabilizer • UV Stabilizer                                                                                                                                                                    |
| Features               | • Chemically Coupled • High Stiffness<br>• Creep Resistant • High Strength<br>• Good Isotropy • Low Emissions • Low Warpage<br>• Heat Stabilized • Low Temperature Impact Resistance • UV Stabilized |
| Uses                   | • Automotive Applications                                                                                                                                                                            |
| RoHS Compliance        | • Contact Manufacturer                                                                                                                                                                               |
| Forms                  | • Pellets                                                                                                                                                                                            |
| Processing Method      | • Injection Molding                                                                                                                                                                                  |
| Resin ID (ISO 1043)    | • PP                                                                                                                                                                                                 |

### ASTM & ISO Properties <sup>1</sup>

| Physical                         | Nominal Value | Unit                  | Test Method    |
|----------------------------------|---------------|-----------------------|----------------|
| Density                          | 1.34          | g/cm <sup>3</sup>     | ISO 1183       |
| Mechanical                       | Nominal Value | Unit                  | Test Method    |
| Tensile Modulus                  | 1.68E+6       | psi                   | ISO 527-2/1A   |
| Tensile Stress (Break)           | 20300         | psi                   | ISO 527-2/1A/5 |
| Tensile Strain (Break)           | 1.8           | %                     | ISO 527-2/1A/5 |
| Flexural Modulus                 |               |                       | ISO 178        |
| 73°F                             | 1.74E+6       | psi                   |                |
| 176°F                            | 1.20E+6       | psi                   |                |
| Flexural Stress                  |               |                       | ISO 178        |
| 73°F                             | 31900         | psi                   |                |
| 176°F                            | 18100         | psi                   |                |
| Impact                           | Nominal Value | Unit                  | Test Method    |
| Charpy Notched Impact Strength   |               |                       | ISO 179/1eA    |
| -22°F                            | 16            | ft·lb/in <sup>2</sup> |                |
| 73°F                             | 15            | ft·lb/in <sup>2</sup> |                |
| Charpy Unnotched Impact Strength |               |                       | ISO 179/1eU    |
| -22°F                            | 28            | ft·lb/in <sup>2</sup> |                |
| 73°F                             | 29            | ft·lb/in <sup>2</sup> |                |

# Celstran® PP-GF50-0455 P10/10

## Celanese Corporation - Polypropylene

| Thermal                                            | Nominal Value | Unit | Test Method |
|----------------------------------------------------|---------------|------|-------------|
| Heat Deflection Temperature (264 psi, Unannealed)  | 316           | °F   | ISO 75-2/A  |
| Heat Deflection Temperature (1160 psi, Unannealed) | 280           | °F   | ISO 75-2/C  |
| Melting Temperature <sup>2</sup>                   | 329           | °F   | ISO 11357-3 |
| Flammability                                       | Nominal Value | Unit | Test Method |
| Flame Rating (0.04 in)                             | HB            |      | UL 94       |

### Processing Information

| Injection              | Nominal Value | Unit |
|------------------------|---------------|------|
| Drying Temperature     | 194 to 212    | °F   |
| Drying Time            | 2.0           | hr   |
| Suggested Max Moisture | 0.20          | %    |
| Rear Temperature       | 446 to 464    | °F   |
| Middle Temperature     | 464 to 482    | °F   |
| Front Temperature      | 482 to 500    | °F   |
| Nozzle Temperature     | 464 to 518    | °F   |
| Processing (Melt) Temp | 464 to 518    | °F   |
| Mold Temperature       | 104 to 158    | °F   |
| Injection Rate         | Slow          |      |
| Back Pressure          | < 435         | psi  |

### Injection Notes

Feeding zone temperature: 20 to 50°C  
 Zone4 temperature: 260 to 270°C  
 Hot runner temperature: 240 to 270°C

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 10°C/min