

Properties**PA66-GF60-01**

Long glass fiber-reinforced PA66 resin (GF60%)

Properties	Test methods	Test conditions	Units	Dry	1.0% moist.
Tensile strength	ISO 527	-	MPa	320	250
Flexural strength	ISO 178	-	MPa	470	360
Flexural modulus	ISO 178	-	MPa	20,000	16,500
Notched Charpy impact strength	ISO 179/1eA	23 deg C	kJ/m ²	60	60
Deflection temperature under load	ISO 75	1.80MPa	deg C	261	-
Density	ISO 1183	-	g/cm ³	1.70	-

Note

•Values are typical, not quality assured.

Typical settings for processing

Preliminary drying	Barrel temperature(deg C)				Screw rotation (rpm)	Back pressure (MPa)	Mold temperature (deg C)
	Nozzle	Front	Middle	Back			
3-5hrs 80-85deg C	270-300	280-320	280-320	280-320	40-60	5-10	60-120