

Properties

S7600

Flame retardant PC/ABS resin (UL94 V-0)

*The product(s) do not contain halogenated compounds as flame retardants and do not contain antimony compounds.

High flow

Properties	Test methods	Test conditions	Units	
Melt mass-flow rate	ISO 1133	240 deg C/5kg	g/10min	40
Mold shrinkage	ASTM D955	-	%	0.4-0.6
Tensile strength	ISO 527	-	MPa	60
Flexural strength	ISO 178	-	MPa	94
Flexural modulus	ISO 178	-	MPa	2700
Notched Charpy impact strength	ISO 179/1eA	23 deg C	kJ/m2	9
Deflection temperature under load	ISO 75	1.80MPa	deg C	80
Flammability	UL94	-	-	V-0/1.2mm 5VB/2.0mm 5VA/2.5mm
Water absorption	ISO 62	-	%	0.3
Density	ISO 1183	-	g/cm3	1.18

Note

- Values are typical, not quality assured.
- UL recognition File No. of Daicel Polymer is E47773.

Typical settings for processing

Preliminary drying	Barrel temperature(deg C)				Screw rotation (rpm)	Back pressure (MPa)	Mold temperature (deg C)
	Nozzle	Front	Middle	Back			
3-5hrs 80-90deg C	250-280	250-280	240-270	220-260	50-80	5-20	50-70