



DAI-EL_{TM} G-751

DAI-EL G-751 is a fluoroelastomer comprising copolymer of vinylidene fluoride and hexafluoropropylene, and containing a curing agent (bisphenol AF) and cure accelerator. This material provides excellent roll processability and metal adhesion.

1. Properties of raw gum

Items	Data	Test method
Color	Milky white or light yellow	Visual observation
Fluorine content	66wt%	
Specific gravity (23°C)	1.81	JIS K 6268
Mooney viscosity (ML 1 + 10•100°C)	Approx. 53	JIS K 6300-1
Solubility	Soluble in low molecular weight ketones and esters	—

2. Physical properties (Cured)

Items	Unit	Data	Test method/condition
100% modulus	MPa	4.9	JIS K 6251
Tensile strength	MPa	14.2	JIS K 6251
Elongation	%	190	JIS K 6251
Compression set	%	18	200°C × 70h, 25% compression
Hardness (Shore A)	—	72	Peak value

* The above numeric values are representative and not guaranteed.

(Compound formulation)

DAI-EL G-751	100 parts		
MT carbon black ^{*1}	20 parts	^{*1} Thermax N990	Cancarb Ltd.
Calcium hydroxide ^{*2}	6 parts	^{*2} Caldic 2000	Ohmi Chemical Industry Co., Ltd.
Magnesium hydroxide (High active) ^{*3}	3 parts	^{*3} Kyowa Mag 150	Kyowa Chemical Industrial Co., Ltd.

(Cure conditions)

Press cure	170°C × 15min
Oven cure	230°C × 24h

3. Handling method/Safety information

Be sure to read the notes stated in MSDS and labels before use.

This product is supplied for general industry and therefore its adequacy and safety for medical applications cannot be guaranteed.

4. Packing specification 20kg

DAIKIN INDUSTRIES, LTD.
Chemical Division
Umeda Center Bldg.,
2-4-12, Nakazaki-Nishi, Kita-ku,
Osaka 530-8323, Japan
Phone: +81-6-6373-4342
Facsimile: +81-6-6373-4390
<http://www.daikin.com/chm>

DAIKIN AMERICA, INC.
20 Olympic Drive,
Orangeburg, NY 10962, USA
Phone: +1-845-365-9500
Toll-Free: +1-800-365-9570
Facsimile: +1-845-365-9598
<http://www.daikin-america.com>

DAIKIN CHEMICAL EUROPE
GmbH
Immermannstr. 65D,
40210 Dusseldorf, Germany
Phone: +49-211-179225-0
Facsimile: +49-211-1640732
<http://www.daikinchem.de>