



Fluoropolymer coating

Primer (Solvent-based)

TC Series

The fluoropolymer coating cannot be applied to base materials due to non-stick property which is a characteristic of fluoropolymer.

Daikin offers several types of primer coating depending on the purpose of use. In particular, when considering a primer for PFA and FEP powder coatings, please use the following primers according to the film thickness of the powder coating.

1. Product Number

For thin film

	Appearance of coating film	Viscosity (sec/25°C·Ford Cup#4)	Solid content (mass%)
TC-1509M1	Black	28~53	22.0~29.0
TC-1559M2	Grayish black	10~35	21.0~28.0

For thick film

	Appearance of coating film	Viscosity (cP)	Solid content (mass%)
TC-11000	Ochre	180~450	38.0~45.0

2. Handling method /Safety information

Be sure to read the cautions written on the MSDS and label.

3. Packaging

Container: Polyethylene bottle, Weight: 10kg

- The products described in this material are supplied for use by general industry, not designed and manufactured for medical purposes. Their adequacy and safety for medical use has not been tested, and cannot be assured by our company. With this in mind, for medical use, you must judge the applicability of use for medical purpose yourself based on testing, the views of medical experts, and legal restrictions of the authorities concerned. Also, if you use products for such purposes, we will only provide them if you consent to the conditions and contents of the contracts which we offer.
- The data released in this material represent one example of the actual value, and the example of usage written in this material does not guarantee the results of application of this product for such usage.

DAIKIN INDUSTRIES, LTD.
Chemical Division
Umeda Center Bldg.,
2-4-12, Nakazaki-Nishi, Kita-ku,
Osaka 530-8323, Japan
Phone: +81-6-6373-4342
Facsimile: +81-6-6373-4390
<http://www.daikin.com/chm>

DAIKIN AMERICA, INC.
20 Olympic Drive,
Orangetburg, NY 10962, USA
Phone: +1-845-365-9500
Toll-Free: +1-800-365-9570
Facsimile: +1-845-365-9598
<http://www.daikin-america.com>

DAIKIN CHEMICAL EUROPE
GmbH
Immermannstr. 65D,
40210 Dusseldorf, Germany
Phone: +49-211-179225-0
Facsimile: +49-211-1640732
<http://www.daikinchem.de>