



# ENFLEX® V1067A BLK UV

ENPLAST Americas, a Ravago Group Company - Thermoplastic Vulcanizate

Wednesday, November 6, 2019

## General Information

### Product Description

Enflex V1067A BLK UV TPV (thermoplastic vulcanizate) is a fully weatherable black EPDM/PP compound. It is designed to replace thermoset elastomers such as EPDM or polychloroprene, and traditional thermoplastic TPVs. Enflex V grades provide the performance of vulcanized rubber with the advantage of low-cost thermoplastic processing.

### General

Material Status	<ul style="list-style-type: none"> <li>Commercial: Active</li> </ul>		
Availability	<ul style="list-style-type: none"> <li>North America</li> </ul>		
Features	<ul style="list-style-type: none"> <li>Acid Resistant</li> <li>Alcohol Resistant</li> <li>Base Resistant</li> <li>Detergent Resistant</li> <li>Good Heat Resistance</li> </ul>	<ul style="list-style-type: none"> <li>Good Processability</li> <li>Good Weather Resistance</li> <li>Low Compression Set</li> <li>Oil Resistant</li> <li>Ozone Resistant</li> </ul>	<ul style="list-style-type: none"> <li>Recyclable Material</li> <li>Solvent Resistant</li> <li>UV Resistant</li> </ul>
Automotive Specifications	<ul style="list-style-type: none"> <li>CHRYSLER MS-AR-100 BGV Color: BLK UV</li> <li>GMW15813P-TPV(EPDM+PP) Type 5</li> </ul>		
Appearance	<ul style="list-style-type: none"> <li>Black</li> </ul>		
Processing Method	<ul style="list-style-type: none"> <li>Extrusion</li> </ul>	<ul style="list-style-type: none"> <li>Injection Molding</li> </ul>	

## ASTM & ISO Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.972		ASTM D792
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	406	psi	ASTM D412
Tensile Strength (Break)	1160	psi	ASTM D412
Tensile Elongation (Break)	590	%	ASTM D412
Tear Strength <sup>2</sup>	166	lbf/in	ASTM D624
Compression Set			ASTM D395
158°F, 22 hr	30	%	
257°F, 70 hr	45	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 5 sec, Extruded	64		
Shore A, 5 sec, Injection Molded	67		
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-76.0	°F	ASTM D746
Melting Temperature	318	°F	ASTM D1238
Dynamic Service Temperature	266	°F	

## Processing Information

Injection	Nominal Value	Unit
Drying Temperature	180	°F
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	0.080	%
Rear Temperature	350 to 370	°F
Middle Temperature	360 to 380	°F

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

# ENFLEX® V1067A BLK UV

ENPLAST Americas, a Ravago Group Company - Thermoplastic Vulcanizate

Injection	Nominal Value	Unit
Front Temperature	370 to 390	°F
Nozzle Temperature	390 to 430	°F
Processing (Melt) Temp	390 to 446	°F
Mold Temperature	50 to 122	°F
Injection Pressure	750 to 1300	psi
Injection Rate	Fast	
Screw Speed	50 to 200	rpm
Clamp Tonnage	3.0 to 5.0	tons/in <sup>2</sup>
Cushion	0.200 to 0.500	in

## Injection Notes

Holding Time: 5 to 7 Sec.

Cooling Time: 30 to 50 Sec.

Extrusion	Nominal Value	Unit
Hopper Temperature	320 to 356	°F
Cylinder Zone 1 Temp.	340 to 375	°F
Cylinder Zone 2 Temp.	340 to 375	°F
Cylinder Zone 3 Temp.	340 to 375	°F
Cylinder Zone 4 Temp.	340 to 375	°F
Cylinder Zone 5 Temp.	340 to 375	°F
Adapter Temperature	375 to 410	°F
Melt Temperature	375 to 390	°F
Die Temperature	375 to 410	°F
Screw L/D Ratio	24.0:1.0	

## Extrusion Notes

Screw: L/D 20:1 or greater (L/D 24:1 preferred)

Compression Zone: 355 - 390°F (180 - 200°C)

Metering Zone: 375 to 410°F (190 to 210°C)

Cooling Water: 60 - 85°F (15 - 30°C)

Screw Speed: 100 - 200 rpm

Screen Pack: 20/40/60

## Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> Die C