



## EZPRENE® 9065A

ENPLAST Americas, a Ravago Group Company - Thermoplastic Vulcanizate

Wednesday, November 6, 2019

### General Information

#### Product Description

65 Shore A TPE (Thermoplastic Vulcanizate). Available in black, natural or pre-colored for injection molding and extrusion applications. This material is non-hygroscopic and offers excellent chemical resistance and physical properties. EZPrene is polyolefin based and is 100% recyclable.

#### General

Material Status	<ul style="list-style-type: none"> <li>Commercial: Active</li> </ul>		
Availability	<ul style="list-style-type: none"> <li>North America</li> </ul>		
Features	<ul style="list-style-type: none"> <li>Chemical Resistant</li> <li>Good Adhesion</li> <li>Good Colorability</li> </ul>	<ul style="list-style-type: none"> <li>Low Die Swell</li> <li>Low to No Water Absorption</li> <li>Ozone Resistant</li> </ul>	<ul style="list-style-type: none"> <li>Recyclable Material</li> <li>UV Resistant</li> </ul>
Automotive Specifications	<ul style="list-style-type: none"> <li>GM GMW15816 Type 5 Color: BLK/NAT</li> </ul>		
Appearance	<ul style="list-style-type: none"> <li>Black</li> </ul>	<ul style="list-style-type: none"> <li>Colors Available</li> </ul>	<ul style="list-style-type: none"> <li>Natural Color</li> </ul>
Processing Method	<ul style="list-style-type: none"> <li>Extrusion</li> </ul>	<ul style="list-style-type: none"> <li>Injection Molding</li> </ul>	

### ASTM & ISO Properties <sup>1</sup>

	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.932		ASTM D792
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	392	psi	ASTM D412
Tensile Strength (Break)	725	psi	ASTM D412
Tensile Elongation (Break)	490	%	ASTM D412
Tear Strength	137	lbf/in	ASTM D624
Compression Set			ASTM D395
73°F, 22 hr	30	%	
257°F, 70 hr	53	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 5 sec, Extruded	65		
Shore A, 5 sec, Injection Molded	67		
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-76.0	°F	ASTM D746
Dynamic Service Temperature	266	°F	
Additional Information	Nominal Value	Unit	Test Method
Ozone Resistance	Excellent		ASTM D1149

### Processing Information

	Nominal Value	Unit
Injection		
Drying Temperature	180	°F
Drying Time	2.0 to 3.0	hr
Rear Temperature	375 to 400	°F
Middle Temperature	385 to 410	°F
Front Temperature	385 to 410	°F
Nozzle Temperature	410 to 430	°F
Processing (Melt) Temp	390 to 430	°F

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

# EZPRENE® 9065A

ENPLAST Americas, a Ravago Group Company - Thermoplastic Vulcanizate

Injection	Nominal Value	Unit
Mold Temperature	75 to 125	°F
Injection Pressure	750 to 1300	psi
Injection Rate	Fast	
Screw Speed	50 to 200	rpm
Clamp Tonnage	2.0 to 3.5	tons/in <sup>2</sup>
Cushion	0.200 to 0.500	in

  

Injection Notes
Holding Time: 5 to 7 Sec.
Cooling Time: 30 to 50 Sec.

  

Extrusion	Nominal Value	Unit
Hopper Temperature	330 to 350	°F
Cylinder Zone 1 Temp.	340 to 375	°F
Cylinder Zone 2 Temp.	340 to 375	°F
Cylinder Zone 3 Temp.	340 to 375	°F
Cylinder Zone 4 Temp.	340 to 375	°F
Cylinder Zone 5 Temp.	340 to 375	°F
Adapter Temperature	375 to 410	°F
Melt Temperature	375 to 390	°F
Die Temperature	375 to 410	°F
Screw L/D Ratio	24.0:1.0	

## Extrusion Notes

Compression Zone: 355 - 390°F (180 - 200°C)

Metering Zone: 375 to 410°F (190 to 210°C)

Screw Speed: 30 - 80 rpm

Screen Pack: 20/40/60

## Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.