



EZPRENE® 9565A PA

ENPLAST Americas, a Ravago Group Company - Thermoplastic Vulcanizate

Wednesday, November 6, 2019

General Information

Product Description

65 Shore A TPE (Thermoplastic Vulcanizate) boundable to nylon. Available in black, natural for injection molding applications with long flow lengths or requires highly cosmetic surface. This soft, easy to color material is non-hygroscopic and offers excellent chemical resistance and physical properties. EZPrene 9500 series materials are polyolefin based and 100% recyclable.

General

Material Status	<ul style="list-style-type: none"> Commercial: Active 		
Availability	<ul style="list-style-type: none"> North America 		
Features	<ul style="list-style-type: none"> Chemical Resistant Fatigue Resistant Good Adhesion 	<ul style="list-style-type: none"> Good Colorability Low to No Water Absorption Ozone Resistant 	<ul style="list-style-type: none"> Recyclable Material Soft UV Resistant
Appearance	<ul style="list-style-type: none"> Black 	<ul style="list-style-type: none"> Natural Color 	
Processing Method	<ul style="list-style-type: none"> Injection Molding 		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.942		ASTM D792
Elastomers			
Tensile Stress (100% Strain)	145	psi	ASTM D412
Tensile Strength (Break)	580	psi	ASTM D412
Tensile Elongation (Break)	590	%	ASTM D412
Tear Strength	103	lbf/in	ASTM D624
Hardness			
Durometer Hardness			ASTM D2240
Shore A, 5 sec, Extruded	65		
Shore A, 5 sec, Injection Molded	68		
Thermal			
Brittleness Temperature	-94.0	°F	ASTM D746
Dynamic Service Temperature	257	°F	

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	180	°F
Drying Time	2.0 to 3.0	hr
Rear Temperature	375 to 400	°F
Middle Temperature	385 to 410	°F
Front Temperature	385 to 410	°F
Nozzle Temperature	410 to 430	°F
Processing (Melt) Temp	390 to 430	°F
Mold Temperature	75 to 125	°F
Injection Pressure	750 to 1300	psi
Injection Rate	Fast	
Screw Speed	50 to 200	rpm
Clamp Tonnage	2.0 to 3.5	tons/in ²
Cushion	0.200 to 0.500	in

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

EZPRENE® 9565A PA

ENPLAST Americas, a Ravago Group Company - Thermoplastic Vulcanizate

Injection Notes

Holding Time: 5 to 7 Sec.

Cooling Time: 30 to 50 Sec.

Notes

¹ Typical properties: these are not to be construed as specifications.